


Technical data

DecoBoard MDF plus microPLUS®

Medium-density fibreboard with homogeneous lay-up, decorative melamine resin facing on both sides and an antimicrobial and antiviral surface finish.

Applications



Furniture and interior fitting

Properties



Variety of decors and / or textures




Easy care



Antimicrobial

Certificates



Melamine facing with antimicrobial and antiviral surface microPLUS®

StyleBoard MDF plus

Melamine facing with antimicrobial and antiviral surface microPLUS®

Specification						Unit	Test standard
Nominal thickness	8	10	12	16	18	mm	
Tolerance on thickness	± 0.3 for class 1, 2 $+0.5/-0.3$ for class 3A, 3B, 4 and gloss surfaces					mm	EN 14323
Length- and width tolerance	± 5					mm	EN 14323
Length- and width tolerance (pre-cut panels)	± 2.5					mm	EN 14323
Flatness				≤ 2 ¹⁾	≤ 2 ¹⁾	mm/m	EN 14323
Edge damage	≤ 10					mm	EN 14323
Edge damage (pre-cut panels)	≤ 3					mm	EN 14323
Surface defects (Points)	≤ 2					mm ² /m ²	EN 14323
Surface defects (Defect in the length)	≤ 20					mm/m ²	EN 14323
Resistance to scratching	≥ 1.5 ²⁾					N	EN 14323
Resistance to staining	≥ 3					Rating	EN 14323
Resistance to cracking	≥ 3					Rating	EN 14323
Resistance to abrasion (plain colours)	3A					Class	EN 14323
Resistance to abrasion (printed designs)	1					Class	EN 14323
Resistance to colour change in xenon arc light	min. 4 Grey Scale Grade						EN 14323
Mean density	730 ³⁾	730 ³⁾	730 ³⁾	710 ³⁾	710 ³⁾	kg/m ³	EN 323
Bending strength	25 ³⁾	25 ³⁾	25 ³⁾	23 ³⁾	23 ³⁾	N/mm ²	EN 310

Technical data

DecoBoard MDF plus microPLUS®

Specification						Unit	Test standard
Nominal thickness	8	10	12	16	18	mm	
Bending modulus of elasticity	2,400 ³⁾	2,400 ³⁾	2,400 ³⁾	2,200 ³⁾	2,200 ³⁾	N/mm ²	EN 310
Internal bond	0.55 ³⁾	0.53 ³⁾	0.53 ³⁾	0.48 ³⁾	0.48 ³⁾	N/mm ²	EN 319
Formaldehyde release	E1 E05 CARB Phase 2 / TSCA Title VI						
Reaction to fire (Euroclass)	D-s2,d0 according to EN 13986 dependent on end use (Thickness: ≥ 9 mm / Gross density: ≥ 600 kg/m ³)						

¹⁾ If symmetrical construction

²⁾ Except smooth and matt structures, as well as decors with mother-of-pearl effect

³⁾ Core material

Specification					Unit	Test standard	
Nominal thickness	19	22	25	28	mm		
Tolerance on thickness	±0.3 for class 1, 2 +0.5/-0.3 for class 3A, 3B, 4 and gloss surfaces	±0,5	±0,5	±0,5	mm	EN 14323	
Length- and width tolerance	± 5				mm	EN 14323	
Length- and width tolerance (pre-cut panels)	± 2.5				mm	EN 14323	
Flatness	≤ 2 ¹⁾				mm/m	EN 14323	
Edge damage	≤ 10				mm	EN 14323	
Edge damage (pre-cut panels)	≤ 3				mm	EN 14323	
Surface defects (Points)	≤ 2				mm ² /m ²	EN 14323	
Surface defects (Defect in the length)	≤ 20				mm/m ²	EN 14323	
Resistance to scratching	≥ 1.5 ²⁾				N	EN 14323	
Resistance to staining	≥ 3				Rating	EN 14323	
Resistance to cracking	≥ 3				Rating	EN 14323	
Resistance to abrasion (plain colours)	3A				Class	EN 14323	
Resistance to abrasion (printed designs)	1				Class	EN 14323	
Resistance to colour change in xenon arc light	min. 4 Grey Scale Grade					EN 14323	
Mean density	710 ³⁾				kg/m ³	EN 323	
Bending strength	23 ³⁾	22 ³⁾	22 ³⁾	22 ³⁾	N/mm ²	EN 310	
Bending modulus of elasticity	2,200 ³⁾	2,000 ³⁾	2,000 ³⁾	2,000 ³⁾	N/mm ²	EN 310	
Internal bond	0.48 ³⁾				N/mm ²	EN 319	
Formaldehyde release	E1 E05 CARB Phase 2 / TSCA Title VI						
Reaction to fire (Euroclass)	D-s2,d0 according to EN 13986 dependent on end use (Thickness: ≥ 9 mm / Gross density: ≥ 600 kg/m ³)						

¹⁾ If symmetrical construction

²⁾ Except smooth and matt structures, as well as decors with mother-of-pearl effect

³⁾ Core material

Technical data

DecoBoard MDF plus microPLUS®

Additional information

Product standard	<ul style="list-style-type: none"> EN 14322
Areas of application	<ul style="list-style-type: none"> Health care / hotel, catering, cruise ships / offices and conference rooms / Educational and leisure facilities (schools, kindergartens, libraries, sports halls, fitness studios) / interior design / kitchen
Core material	<ul style="list-style-type: none"> StyleBoard MDF plus Medium-density fibreboard (MDF) according to EN 622-1, with uniform structure.
Product safety	<ul style="list-style-type: none"> This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011. We manufacture the panels without the use of halogens, heavy metals, preservatives, wood protectors or organic solvents.
Antimicrobial effect	<ul style="list-style-type: none"> Surface with antimicrobial effect in 7 h for interior fit-out and finishes – Test Methodology JIS Z 2801 / ISO 22196
Antiviral effect	<ul style="list-style-type: none"> Surface with antiviral effect against enveloped viruses in 24 h for interior fit-out and finishes - Test Methodology ISO 21702:2019
Resistance to heat	<ul style="list-style-type: none"> Heat sources (e.g. coffee machines, printers, fax machines, etc.) should not come into direct contact with the board, otherwise cracks may form due to drying out. For continuous exposure to heat, temperatures of up to 50°C are permissible. In the case of permanent exposure to heat, we expressly draw attention to the risk of cracking.
Special	<ul style="list-style-type: none"> Sanitized® Silver is based on the natural effect of silver, embedded in a patented glass-ceramic. This additive is free of nanoparticles and is incorporated as a dispersion into the resin of our decor / overlay papers. Sanitized® Silver remains in the product and does not wash out. The effect is ensured over the whole life cycle of the product. A protective foil must be removed as soon as possible after processing – but at the latest within 6 months after delivery – to ensure residue-free removal of the foil. In addition, foiled boards must not be exposed to direct sunlight (UV radiation).
Note	<ul style="list-style-type: none"> FSC certification or PEFC certification available on request. FSC license code: FSC® C011773 PEFC license code: PEFC/04-32-0828
Colour and surface match	<ul style="list-style-type: none"> Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2023 Pfleiderer Deutschland GmbH

This information has been compiled with the greatest care. Nevertheless we can assume no liability for the correctness, completeness and up-to-dateness of this information. Colour deviations caused by the printing technology are possible. In view of the ongoing further development and adaptation of our products, possible amendments to the relevant standards, laws and regulations, our technical data sheets and product documentation expressly do not constitute a legally binding assurance of the properties described there. In particular no guarantee of suitability for a concrete application can be derived. It is therefore the personal responsibility of the individual user in all cases to check the processing and suitability of the products described in this document for the intended application in advance, and to take into consideration the legal framework and the respective state-of-the-art. We furthermore expressly draw attention to the applicability of our General Terms and Conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com

Pfleiderer Deutschland GmbH

Ingolstädter Str. 51
92318 Neumarkt
Germany

phone +49 (0) 91 81 28 48 0
Fax +49 (0) 91 81 28 48 2
info@pfleiderer.com
www.pfleiderer.com