

Technical data

DecoBoard Pyroex

Flame resistant particleboard with decorative melamine resin facing on both faces.

Applications



Furniture and interior fitting



Fire protection



Melamine facing

PremiumBoard Pyroex

Melamine facing

Properties



Decorative variety



Easy care



Antimicrobial



Food harmless



Flame retardant



Easy to use and machine

Certificates



Specification						Unit	Test standard
Nominal thickness	10	13	16	18	19	mm	
Tolerance on thickness			+ 0.5, -0.3			mm	EN 14323
Length- and width tolerance			± 5			mm	EN 14323
Length- and width tolerance (pre-cut panels)			± 2.5			mm	EN 14323
Flatness			≤ 2 ¹⁾	≤ 2 ¹⁾	≤ 2 ¹⁾	mm/m	EN 14323
Edge damage			≤ 10			mm	EN 14323
Edge damage (pre-cut panels)			≤ 3			mm	EN 14323
Surface defects (Points)			≤ 2			mm ² /m ²	EN 14323
Surface defects (Defect in the length)			≤ 20			mm/m ²	EN 14323
Resistance to scratching			≥ 1.5 ²⁾			N	EN 14323
Resistance to staining			min. 3			Rating	EN 14323
Resistance to cracking			min. 3			Rating	EN 14323
Resistance to abrasion (plain colours)			min. 2			Class	EN 14323
Resistance to abrasion (printed designs)			min. 1			Class	EN 14323
Resistance to colour change in xenon arc light			min. 4 Grey Scale Grade				EN 14323
Bending strength			11 ³⁾			N/mm ²	EN 310
Bending modulus of elasticity	1,800 ³⁾	1,800 ³⁾	1,600 ³⁾	1,600 ³⁾	1,600 ³⁾	N/mm ²	EN 310
Internal bond	0.4 ³⁾	0.4 ³⁾	0.35 ³⁾	0.35 ³⁾	0.35 ³⁾	N/mm ²	EN 319

Technical data

DecoBoard Pyroex

Specification						Unit	Test standard
Nominal thickness	10	13	16	18	19	mm	
Surface soundness	0.8 ³⁾					N/mm ²	EN 311
Formaldehyde release	E1 E05						
Reaction to fire (Euroclass)	B-s2,d0						EN 13501-1
Reaction to fire	flame retardant						

¹⁾ If symmetrical construction

²⁾ Except smooth and matt structures, as well as decors with mother-of-pearl effect

³⁾ Core material

Specification					Unit	Test standard
Nominal thickness	22	25	28	38	mm	
Tolerance on thickness	± 0.5				mm	EN 14323
Length- and width tolerance	± 5				mm	EN 14323
Length- and width tolerance (pre-cut panels)	± 2.5				mm	EN 14323
Flatness	≤ 2 ¹⁾				mm/m	EN 14323
Edge damage	≤ 10				mm	EN 14323
Edge damage (pre-cut panels)	≤ 3				mm	EN 14323
Surface defects (Points)	≤ 2				mm ² /m ²	EN 14323
Surface defects (Defect in the length)	≤ 20				mm/m ²	EN 14323
Resistance to scratching	≥ 1.5 ²⁾				N	EN 14323
Resistance to staining	min. 3				Rating	EN 14323
Resistance to cracking	min. 3				Rating	EN 14323
Resistance to abrasion (plain colours)	min. 2				Class	EN 14323
Resistance to abrasion (printed designs)	min. 1				Class	EN 14323
Resistance to colour change in xenon arc light	min. 4 Grey Scale Grade					EN 14323
Bending strength	10.5 ³⁾	10.5 ³⁾	10.5 ³⁾	8.5 ³⁾	N/mm ²	EN 310
Bending modulus of elasticity	1,500 ³⁾	1,500 ³⁾	1,500 ³⁾	1,200 ³⁾	N/mm ²	EN 310
Internal bond	0.3 ³⁾	0.3 ³⁾	0.3 ³⁾	0.2 ³⁾	N/mm ²	EN 319
Surface soundness	0.8 ³⁾				N/mm ²	EN 311
Formaldehyde release	E1 E05					
Reaction to fire (Euroclass)	B-s2,d0					EN 13501-1
Reaction to fire	flame retardant					

¹⁾ If symmetrical construction

²⁾ Except smooth and matt structures, as well as decors with mother-of-pearl effect

³⁾ Core material

Technical data

DecoBoard Pyroex

Additional information

Product standard	<ul style="list-style-type: none"> • EN 14322
Areas of application	<ul style="list-style-type: none"> • Preventive fire protection in the decorative sector. For interior fitting as wall and ceiling coverings, installations, room dividers and furniture, in industrial and administrative buildings, schools, sports and festival halls, hotels and care facilities.
Core material	<ul style="list-style-type: none"> • PremiumBoard Pyroex • Flame resistant particleboard, suitable for non load-bearing purposes in dry areas, for interior fitting and for furniture subject to higher demands on fire protection.
Product safety	<ul style="list-style-type: none"> • This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. • The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011. • We manufacture the panels without the use of halogens, heavy metals, preservatives, wood protectors or organic solvents.
Antimicrobial effect	<ul style="list-style-type: none"> • Surface with antimicrobial effect in 24h for interior fit-out and finishes - Test Methodology JIS Z 2801 / ISO 22196
Resistance to heat	<ul style="list-style-type: none"> • Heat sources (e.g. coffee machines, printers, fax machines, etc.) should not come into direct contact with the board, otherwise cracks may form due to drying out. For continuous exposure to heat, temperatures of up to 50°C are permissible. In the case of permanent exposure to heat, we expressly draw attention to the risk of cracking.
Note	<ul style="list-style-type: none"> • FSC®-certification (license code: FSC® C011773) or PEFC-certification (license code: PEFC/04-32-0828) - available on request.
Colour and surface match	<ul style="list-style-type: none"> • Decor, structure and core board all influence the final appearance of the end product. • Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. • The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. • To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2021 Pfleiderer Deutschland GmbH

This information has been compiled with the greatest care. Nevertheless we can assume no liability for the correctness, completeness and up-to-dateness of this information. Colour deviations caused by the printing technology are possible. In view of the ongoing further development and adaptation of our products, possible amendments to the relevant standards, laws and regulations, our technical data sheets and product documentation expressly do not constitute a legally binding assurance of the properties described there. In particular no guarantee of suitability for a concrete application can be derived. It is therefore the personal responsibility of the individual user in all cases to check the processing and suitability of the products described in this document for the intended application in advance, and to take into consideration the legal framework and the respective state-of-the-art. We furthermore expressly draw attention to the applicability of our General Terms and Conditions.