

Declaration of Conformity – Ref.No 444670

In compliance with the Construction Products Regulation and The Construction Products (Amendment etc.) (EU Exit) Regulations 2020.

1. Identification code of product-type	LivingBoard P4 – 444670
2. Intended use	Load-bearing boards for use in dry conditions.
3. Manufacturer	Pfleiderer Deutschland GmbH, Ingolstädter Str. 51, D – 92318 Neumarkt
4. Authorised representative	not relevant
5. System of assessment and verification	System 2+
6. Assessment of performance	This Certificate attests that all provisions concerning the assessment and verification of constancy of performance described in the EN: BS EN 13986:2004 + A1 2015 under system 2+ for the performances set out in the certificate UK 0836-CPR-22/F6272 are applied and that the factory production control fulfils all the prescribed requirements for these performances.
7. European Technical Assessment	not relevant

8. Declared performance

Essential characteristics/main features	Thickness	Unit	Declared performance					Harmonised technical specification	
			> 10 mm to ≤ 13 mm	> 13 mm to ≤ 20 mm	> 20 mm to ≤ 25 mm	> 25 mm to ≤ 32 mm	> 32 mm to ≤ 40 mm		> 40 mm
Strength, tension (ft)	N/mm ²		8.9	7.9	6.9	6.1	5.0	4.4	EN 13986:2004 +A1:2015
Strength, compression (fc)	N/mm ²		12.0	11.1	9.6	6.1	7.6	6.1	
Strength, bending (fm)	N/mm ²		14.2	12.5	10.8	9.2	7.5		
Stiffness, panel shear (fv)	N/mm ²		6.6	6.1	5.5	4.8	4.4	4.2	
Stiffness, planar shear (fr)	N/mm ²		1.8	1.6	1.4	1.2	1.1	1.0	
Punching shear as point load strenght			NPD						
Punching shear as point load stiffness			NPD						
Racking resistance			NPD						
Impact resistance			NPD						
Reaction to fire			D-s2,d0 conforming to EN 13986 dependent on end use (Thickness: ≥ 9 mm / Gross density: ≥ 600 kg/m ³)						
Water vapour permeability, wet cup μ			50						
Water vapour permeability, dry cup μ			100						
Class, formaldehyde release			E1 E05						
Release (Content), pentachlorophenol (PCP)	mg/kg		< 3						
Airborne sound insulation (surface mass)			NPD						
Sound Absorption frequency range 250 Hz to 500 Hz			0.1						
Sound Absorption frequency range 1000 Hz to 2000 Hz			0.25						
Thermal conductivity (density)	W/(mK)		0.12						
Embedment strength			NPD						
Air permeability			NPD						
Internal bond	N/mm ²		0.4	0.35	0.3	0.25	0.2		
Swelling in thickness, 24 h	%		16	15			14	NPD	
Internal bond after boil test			NPD						
Factor of modification (kmod)			NPD						
Factor of distortion (kdef)			NPD						

9. The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 8. This Declaration of Conformity is issued under the sole responsibility of the manufacturer identified in point 3.

Signed for and on behalf of the manufacturer by:

Date of issue: 2024-09-24

i. V. Claus Seemann
Head of productmanagement core materials
(Document was created electronically and is therefore valid without signature!)

NPD: performance not defined