DUROPAL | thermopal

PFLEIDERER

Declaration of Performance (CE) – Ref.No 6132

acc. to REGULATION (EU) No 305/2011 Article 4

1. Identification code of product-type	PremiumBoard Pyroex P6, DecoBoard Pyroex P6 – 6132
2. Intended use	Heavy duty load-bearing boards for use in dry conditions.
3. Manufacturer	Pfleiderer Deutschland GmbH, Ingolstädter Str. 51, D – 92318 Neumarkt
4. Authorised representative	not relevant
5. System of assessment and verification	System 2+
6. Assessment of performance	The notified body Fraunhofer-Institut für Holzforschung Wilhelm-Klauditz-Institut WKI, Riedenkamp 3, 38108 Braunschweig, Deutschland has issued the certificate 0765-CPR-1260 (P6) about the product conformity according system 2+ based on the following: The certificate confirms, that all provisions concerning assessment and surveillance of the continuous performance described in annex ZA of the harmonized standard EN 13986:2004+A1:2015 according system 2+ are applied and that the factory production control fulfills all in it stipulated requirements.
7. European Technical Assessment	not relevant

DUROPAL | thermopal

PFLEIDERER

8. Declared performance

		Thickness	38 mm	
Essential characteristics/main features	*Unit*	*Declared performance*	*Harmonised technical specification*	
Strength, tension (ft)	N/mm²	7.8	EN 13986:2004 +A1:2015	
Strength, compression (fc)	N/mm²	11.9		
Strength, bending (fm)	N/mm²	11.7		
Stiffness, panel shear (fv)	N/mm²	6.0		
Stiffness, planar shear (fr)	N/mm²	1.7		
Punching shear as point load strenght		NPD		
Punching shear as point load stiffness		NPD		
Racking resistance		NPD		
Impact resistance		NPD		
Reaction to fire		B-s2,d0		
Water vapour permeability, wet cup μ		15		
Water vapour permeability, dry cup μ		50		
Class, formaldehyde release		E1 E05		
Release (Content), pentachlorophenol (PCP)	mg/kg	< 3		
Airborne sound insulation (surface mass)		NPD		
Sound Absorption frequency range 250 Hz to 500 Hz		0.1		
Sound Absorption frequency range 1000 Hz to 2000 Hz		0.25		
Thermal conductivity (density)	W/(mK)	0.12		
Embedment strength		NPD		
Air permeability - 50 Pa		NPD		
Internal bond	N/mm²	0.3		
Swelling in thickness, 24 h	%	NPD		
Internal bond after boil test		NPD		
Factor of modification (kmod)		NPD		
Factor of distortion (kdef)		NPD		

9. The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 8. This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3.

Signed for and on behalf of the manufacturer by:

Date of issue: 2026-09-01

i. V. Claus Seemann
Head of productmanagement core materials
(Document was created electronically and is therefore valid without signature!)

NPD: performance not defined
Technical values refer to the core material