

## PRODUCT INFORMATION

Resistance to disinfectant, stain resistance and chemical resistance of Duropal Laminates



## RESISTANCE TO DISINFECTANT

Duropal laminates display high resistance to disinfectants. This permits a regular and thorough cleaning in accordance with applicable hygiene regulations.

The ease-of-cleaning and good disinfectibility is favoured by the fact that laminate surfaces consist of thermosetting resin which form a stable, resistant and a material beyond reactivation. The surface is also completely closed i.e. free of pores, which means that dirt and germs cannot settle permanently.

The test of disinfectant resistance is carried out analogously to the determination of stain resistance according to EN 438-2. The surface is brought into contact with different substances, the duration and conditions of contact are specified in the standard for each substance.

At the end of the recommended exposure time, which is 16 hours for disinfectants, the laminate surface is washed up and examined for permanent traces on the surface. The results are categorised into five grades:

- Level 5: No visible change
- Level 4: Slight change of gloss level and/or colour which is only visible under certain viewing angles
- Level 3: Moderate change of gloss level and/or colour
- Level 2: Clear change of gloss level and/or colour
- Level 1: Damage of the surface and/or blistering

If other disinfectants than those listed below are intended to come into contact with Duropal laminates, their compatibility must be checked in each individual case.

November 22

## Pfleiderer Lab Test Assessments:

Manufacturer	Product	Concentration	Level
B. Braun SE	Helipur 1l	4%	5
B. Braun SE	Melsept® SF	/	5
BODE Chemie GmbH	Dismozon® plus	/	5
BODE Chemie GmbH	Bacillof AF	/	5
clinell	UNIVERSAL WIPES	/	5
Dr. Johnson´s	Sterilising Fluid, highly concentrated	2,2%	5
Dr. Nüsken Chemie GmbH	NÜSCOSEPT	4%	5
DR. SCHNELL GmbH & Co. KGaA	FOROL fruit Universalreiniger	2%	5
DR. SCHNELL GmbH & Co. KGaA	FLOORTOP Hochleistungs-Wischpflege	/	5
DR. SCHNELL GmbH & Co. KGaA	DESIFOR PROTECT	/	5
Dr. Schumacher GmbH	OPTISEPT®	/	5
Dr. Schumacher GmbH	Ultrasol® F	/	5
ECOLAB	Brial TOP SCHONREINIGER	5%	5
ECOLAB	Desguard 20	0,5%	5
ECOLAB	Desguard 20	3%	5
ECOLAB	Incidin™ Active	2%	5
ECOLAB	Incidin™ Plus	8%	5
ECOLAB	Incidin™ Pro	4%	5
ECOLAB	Incidin™ Pro	100%	5
ECOLAB	Incidin™ Rapid	0,5%	5
ECOLAB	Incidin™ Rapid	2%	5
ECOLAB	Klercide Sporicidal Active	100%	5
ECOLAB	Klercide Low Residue Quat	100%	5
ECOLAB	Klercide 70/30 IPA	100%	5
ECOLAB	Klercide Neutral Detergent	100%	5
KESLA HYGIENE AG	Wofasteril®	1%	5
KESLA HYGIENE AG	Wofasteril® Kombiverfahren – Wofasteril und Alcapur	2%	5
Lysoform Dr. Hans Rosemann GmbH	Amocid®	5%	5
Lysoform Dr. Hans Rosemann GmbH	Clorina®	/	5
Lysoform Dr. Hans Rosemann GmbH	Trichlorol®	5%	5
Lysoform Dr. Hans Rosemann GmbH	Aldasan® 2000	/	5
Lysoform Dr. Hans Rosemann GmbH	Lysoformin® Plus	2%	5
MENNO CHEMIE-VERTRIEB GmbH	NEOPREDISAN 135-1	/	5
PAUL HARTMANN AG	Dismozon plus	0,8%, 1,2%	5
Redditch Medical Ltd.	InSpec™ HA	/	5

November 22

Schülke & Mayr GmbH	antifect® extra	0,7%, 2,5%	5
Schülke & Mayr GmbH	perform®	3%	5
Schülke & Mayr GmbH	pursept® AF	2 %	5
Schülke & Mayr GmbH	terralin® PAA	8%	5
Schülke & Mayr GmbH	mikrozid® AF wipes	/	5
Schülke & Mayr GmbH	mikrozid® universal wipes	/	5
Tristel GmbH	JET by Cache	/	5

None of the tested disinfectants led to a change in the Duropal laminate.

Since the nature and composition of disinfectants are generally not known, it is advisable to remove these substances after the recommended exposure time has been reached. For said reasons a general release of disinfectants is not possible.

Therefore, before first use, a test is advisable at a non-visible point.

## STAIN RESISTANCE

The test for stain resistance is carried out in the same way as the test for disinfectant resistance in accordance with EN 438-2. The procedure and evaluation of results can be found in the previous section. The substances and respective exposure times are part of the table below.

For the degree of stain resistance of Duropal products, please refer to the respective technical data sheet.

Stain-producing substances	Exposure time
<b>Group 1</b> <ul style="list-style-type: none"> <li>• Acetone</li> <li>• Other organic solvents</li> <li>• Toothpaste</li> <li>• Hand cream</li> <li>• Urine</li> <li>• Alcoholic beverages</li> <li>• Natural fruit and vegetable juices</li> <li>• Lemonade and fruit drinks</li> <li>• Meats and sausages</li> <li>• Animal and vegetable fats and oils</li> <li>• Water</li> <li>• Yeast suspension in water</li> </ul>	16 h
<ul style="list-style-type: none"> <li>• Salt solutions (NaCl)</li> <li>• Mustard</li> <li>• Lyes, soap solutions</li> <li>• Cleaning solution consisting of: 23 % dodecylbenzene sulfonate 10 % alkyl aryl polyglycol ether 67 % water</li> <li>• Commercial disinfectants</li> <li>• Stain or paint removers based on organic solvents</li> <li>• Citric acid (10% solution)</li> </ul>	
<b>Group 2</b> <ul style="list-style-type: none"> <li>• Coffee (120g of coffee per litre of water)</li> <li>• Black tea (9g of tea per litre of water)</li> <li>• Milk (all types)</li> <li>• Wine vinegar</li> <li>• Alkaline-based cleaning agents (to 10% concentration with water)</li> <li>• Hydrogen peroxide (3% solution)</li> </ul>	16 h
<ul style="list-style-type: none"> <li>• Ammonia (10% solution of commercial concentrate)</li> <li>• Nail varnish</li> <li>• Nail varnish remover</li> <li>• Lipstick</li> <li>• Water colours</li> <li>• Laundry marking inks</li> <li>• Ball point inks</li> </ul>	

November 22

<b>Group 3</b> <ul style="list-style-type: none"> <li>• Sodium hydroxide (25% solution)</li> <li>• Hydrogen peroxide (30% solution)</li> <li>• Concentrated vinegar (30% acetic acid)</li> <li>• Bleaching agents and sanitary cleaners containing them</li> <li>• Hydrochloric acid based cleaning agents (<math>\leq 3\%</math> HCl)</li> <li>• Acid-based metal cleaners</li> <li>• Iodine</li> <li>• Hair colouring and bleaching agents</li> </ul>	<ul style="list-style-type: none"> <li>• Soot suspension in paraffin oil (shoe polish replica)</li> <li>• Boric acid</li> <li>• Lacquers and adhesives (except fast curing materials)</li> <li>• Amidosulfonic acid descaling agents (<math>&lt; 10\%</math> solution)</li> <li>• Mercurochrome (2,7-dibromo-4-hydroxymercurifluorescein, disodium salt)</li> </ul>	10 min
---	---	--------

## CHEMICAL RESISTANCE

Duropal laminates are resistant to most chemicals. However, some chemicals can affect the surface. The decisive factors are the concentration of the chemical, the pH value, the exposure time and the temperature.

Since the nature and composition of chemicals are not always known, they must always be removed immediately from the decorative laminate surface.

The substances listed in the following table do not lead to any change in the melamine surface even after a longer exposure time  $\geq 16$  hours:

Substances not causing any alteration on laminate surfaces	
<b>A</b>	Asparagine $C_4H_8N_2O_3$
Acetic acid $CH_3COOH$	Aspartic acid $C_4H_7NO_4$
Acetic acid iso-amyl ester $C_7H_{14}O_2$	<b>B</b>
Acetone $C_3H_6O$	Barium chloride $BaCl_2$
Alcohols (any) ROH	Barium sulphate $BaSO_4$
Alcoholic beverages ROH	Benzaldehyde $C_7H_6O$
Aldehydes RCHO	Benzidine $NH_2C_6H_4C_6H_4NH_2$
Aluminium sulphate $Al_2(SO_4)_3$	Benzoic acid $C_7H_6O_2$
Alum solution $KAl(SO_4)_3$	Benzene $C_6H_6$
Amides $RCONH_2$	Blood/Blood Group Test Sera
Amines (any)	Boric acid $H_3BO_3$
4-Aminoacetophenone $C_8H_9NO$	Butylacetat $C_6H_{12}O_2$
Ammonia $NH_3$	Butyl alcohol $C_4H_{10}O$
Ammonium chloride $NH_4Cl$	<b>C</b>
Ammonium sulphate $(NH_4)_2SO_4$	Cadmium acetate $Cd(CH_3COO)_2$
Ammonium thiocyanate $NH_4SCN$	Cadmium sulphate $CdSO_4$
Amylacetat $C_7H_{14}O_2$	Calcium carbonate $CaCO_3$
Amyl alcohol $C_5H_{12}O$	Calcium chloride $CaCl_2$
a-Naphthol $C_{10}H_8O$	Calcium hydroxide $Ca(OH)_2$
a-Naphtylamine $C_{10}H_9N$	Calcium nitrate $Ca(NO_3)_2$
Arabinose $C_5H_{10}O_5$	Calcium oxide $CaO$
Ascorbic acid $C_6H_8O_6$	Cane sugar $C_{12}H_{22}O_{11}$

November 22

Carbolic acid $C_6H_6O$	<b>L</b>
Carbol-xylene $C_6H_5OH-C_6H_4(CH_3)_2$	Lactic acid $C_3H_6O_3$
Cement	Lactose $C_{12}H_{22}O_{11}$
Chloral hydrate $C_2H_3Cl_3O_2$	Laevulose $C_6H_{12}O_6$
Chlorobenzene $C_6H_5Cl$	Lead acetate $Pb(C_2H_3O_2)_2$
Cholesterol $C_{27}H_{46}O$	Lead nitrate $Pb(NO_3)_2$
Citric acid $C_6H_8O_7$	Lithium carbonate $Li_2CO_3$
Cocaine $C_{17}H_{21}NO_4$	Lithium hydroxide up to 10% LiOH
Copper sulphate $CuSO_4$	<b>M</b>
Cresol $C_7H_8O$	Magnesium carbonate $MgCO_3$
Cresylic acid $CH_3C_6H_4COOH$	Magnesium chloride $MgCl_2$
Cyclohexane $C_6H_{12}$	Magnesium hydroxide $Mg(OH)_2$
<b>D</b>	Magnesium sulphate $MgSO_4$
Digitonine $C_{56}H_{92}O_{29}$	Maltose $C_{12}H_{22}O_{11}$
Dimethylformamide $C_3H_7NO$	Mannite $C_6H_{14}O_6$
Dimethyl sulphoxide $C_2H_6OS$	Mannose $C_6H_{12}O_6$
Dioxane $C_4H_8O_2$	Mercury Hg
Dulcitol $C_6H_{14}O_6$	Meso inositol $C_6H_6(OH)_6$
<b>E</b>	Methanol $CH_3OH$
Ethyl acetate $C_4H_8O_2$	Methylene chloride (Dichloromethane) $CH_2Cl_2$
<b>F</b>	Mineral oils
Formaldehyde $CH_2O$	Mineral salts (exception see: Table 3)
Formic acid up to 10% $HCOOH$	<b>N</b>
Fructose/Galactose $C_6H_{12}O_6$	Nail varnish
<b>G</b>	Nail varnish remover
Gelatine	Nickel sulphate $NiSO_4$
Glacial acetic acid / acetic acid $CH_3COOH$	Nicotine $C_{10}H_{14}N_2$
Glucose $C_6H_{12}O_6$	<b>O</b>
Glycerine $C_3H_8O_3$	Octanol (octyl alcohol) $C_8H_{18}O$
Glycocoll $C_2H_5NO_2$	Oleic acid $C_{18}H_{34}O_2$
Glycol (any) $HOCH_2CH_2OH$	Olive oil
Graphite (carbon) C	<b>P</b>
Gypsum $CaSO_4 \cdot 2H_2O$	Paraffin $C_nH_{2n+2}$
<b>H</b>	Paraffin oil
Heptanol $C_7H_{15}OH$	Pentanol $C_5H_{12}O$
Hexane $C_6H_{14}$	Percaulic acid $HClO_4$
Hexanol $C_6H_{13}OH$	Phenol & phenol derivatives $C_6H_6O$
Hydrogen peroxide 3% $H_2O_2$	Phenolphthalein $C_{20}H_{14}O_4$
Hydroquinone $C_6H_6O_2$	p-Nitrophenol $C_6H_4NO_2OH$
<b>I</b>	Potassium aluminium sulphate $KAl(SO_4)_2$
Ink	Potassium bromate $KBrO_3$
Inorganic salts and their mixtures	Potassium bromide KBr
Inositol $C_6H_{12}O_6$	Potassium carbonate $K_2CO_3$
Isopropyl $C_3H_8O$	Potassium chloride KCl
<b>K</b>	Potassium hexacyanoferrate $K_4Fe(CN)_6$
Ketones (any) $RCOR$	Potassium hydroxide (potash lye) up to 10% KOH

November 22

Potassium iodate $KIO_3$	Starch
Potassium nitrate $KNO_3$	Stearic acid $C_{18}H_{36}O_2$
Potassium sodium tartrate $KNaC_4H_4O_6 \cdot 4H_2O$	Styrene $C_8H_8$
Potassium sulphate $K_2SO_4$	Sulphur S
Potassium tartrate $C_4H_4K_2O_6$	<b>T</b>
1,2-Propanediol $C_3H_8O_2$	Talk $Mg_3Si_4O_{10}(OH)_2$
Propanol $C_3H_7OH$	Tannin $C_{76}H_{52}O_{46}$
Pyridine $C_5H_5N$	Tetrachloromethane $CCl_4$
<b>R</b>	Tetrahydrofuran $C_4H_8O$
Raffinose $C_{18}H_{32}O_{16}$	Tetralin $C_{10}H_{12}$
Rhamnose $C_6H_{12}O_5$	Thiourea $CH_4N_2S$
<b>S</b>	Thymol $C_{10}H_{14}O$
Salicylaldehyde $C_7H_6O_2$	Toluene $C_7H_8$
Salicylic acid $C_7H_6O_3$	Trehalose $C_{12}H_{22}O_{11}$
Sodium acetate $C_2H_3NaO_2$	Trichloroethylene $C_2HCl_3$
Sodium carbonate $Na_2CO_3$	Tryptophan $C_{11}H_{12}N_2O_2$
Sodium chloride NaCl	Turpentine
Sodium citrate $C_6H_5Na_3O_7$	<b>U</b>
Sodium diethyl barbiturate $NaC_8H_{11}N_2O_3$	Urea solution $CO(NH_2)_2$
Sodium hydrogen carbonate $NaHCO_3$	Uric acid $C_5H_4N_4O_3$
Sodium hydrogen sulphite $NaHSO_3$	<b>V</b>
Sodium hydroxide up to 10% NaOH	Vanillin $C_8H_8O_3$
Sodium hyposulphite $Na_2S_2O_4$	<b>W</b>
Sodium nitrate $NaNO_3$	Water $H_2O$
Sodium phosphate $Na_3PO_4$	Wine acid $C_4H_6O_6$
Sodium silicate $Na_2SiO_3$	<b>X</b>
Sodium sulphate $Na_2SO_4$	Xylene $C_8H_{10}$
Sodium sulphide $Na_2S$	<b>Z</b>
Sodium sulphite $Na_2SO_3$	Zinc chloride $ZnCl_2$
Sodium tartrate $Na_2C_4H_4O_6$	Zinc sulfate $ZnSO_4$
Sodium thiosulfate $Na_2S_2O_3$	Zinc chloride $ZnCl_2$
Sorbitol $C_6H_{14}O_6$	

The following substances may only be used for a short time, maximum 10 to 15 minutes. During this time, the surface must be wiped with a wet cloth and then rubbed dry.

Substances causing laminate surface damage after prolonged exposure	
Aluminium chloride $AlCl_3$	Fuchsine $C_{19}H_{19}N_3O$
Amidosulfonic acid $NH_2SO_3H$	Hydrochloric acid up to 10% HCl
Ammonium hydrogen sulphate $NH_4HSO_4$	Hydrogen peroxide 3-30% $H_2O_2$
Arsenic acid up to approx. 10% $H_3AsO_4$	Inorganic acids up to 10%
Crystal Violet (Gentian Violet) $C_{25}H_{30}ClN_3$	Iodine $I_2$
Dyeing and bleaching agents	Lithium hydroxide over approx.. 10% LiOH
Ferric chloride $FeCl_3$	Mercuric di-chromate $HgCr_2O_7$
Ferrous chloride $FeCl_2$	Methylene Blue $C_{16}H_{18}N_3S$

November 22

Formic acid up to 10% HCOOH	Millon's reagent $\text{OHg}_2\text{NH}_2\text{Cl}$
Nitric acid up to 10% $\text{HNO}_3$	Potassium permanganate $\text{KMnO}_4$
Oxalic acid $\text{C}_2\text{H}_2\text{O}_4$	Silver nitrate $\text{AgNO}_3$
Picric acid $\text{C}_6\text{H}_3\text{N}_3\text{O}_7$	Sodium hydrogen sulphate $\text{NaHSO}_4$
Phosphoric acid up to 10% $\text{H}_3\text{PO}_4$	Sodium hydroxide over 10% $\text{NaOH}$
Potassium chromate $\text{K}_2\text{CrO}_4$	Sodium hypochlorite (chlorine bleach) $\text{NaOCl}$
Potassium di-chromate $\text{K}_2\text{Cr}_2\text{O}_7$	Sodium hypochlorite (chlorine lye) $\text{NaOCl}$
Potassium hydrogen sulphate $\text{KHSO}_4$	Sublimate solution $\text{HgCl}_2$
Potassium hydroxide over 10% $\text{KOH}$	Sulphuric acid up to 10% $\text{H}_2\text{SO}_4$
Potassium iodide $\text{KI}$	

The chemicals listed in the table below cause irreversible laminate surface damages. Any contact, even short-term, must therefore be avoided!

Substances causing irreversible laminate-surface damage	
Adhesives (chemically hardened)	Hydrogen bromide* $\text{HBr}$
Amidosulfonic acid* $\text{NH}_2\text{SO}_3\text{H}$	Inorganic acids*
Aqua regia* $\text{HNO}_3 + \text{HCl} = 1:3$	Nitric acid* $\text{HNO}_3$
Arsenic acid $\text{H}_3\text{AsO}_4$	Phosphoric acid* $\text{H}_3\text{PO}_4$
Chrome sulphuric acid* $\text{K}_2\text{Cr}_2\text{O}_7 + \text{H}_2\text{SO}_4$	Hydrofluoric acid* $\text{HF}$
Formic acid* $\text{HCOOH}$	Sulfuric acid* $\text{H}_2\text{SO}_4$
Hydrochloric acid* $\text{HCl}$	

\* in concentrations over 10%

The influence of aggressive gases can have a negative effect on the optical appearance of Dupopal laminate surfaces, but their functionality is generally not negatively affected.

Substances causing laminate-surface damage
Bromine $\text{Br}_2$
Chlorine $\text{Cl}_2$
fuming acids
Nitrous fumes $\text{NO}_x / \text{N}_x\text{O}_y$
Sulphur dioxide $\text{SO}_2$

## PM HPL/Elemente

© Copyright 2022 Pfleiderer Deutschland GmbH

This information has been compiled with the greatest care. Nevertheless we can assume no liability for the correctness, completeness and up-to-dateness of this information. Colour deviations caused by the printing technology are possible. In view of the ongoing further development and adaptation of our products, possible amendments to the relevant standards, laws and regulations, our technical data sheets and product documentation expressly do not constitute a legally binding assurance of the properties described there. In particular no guarantee of suitability for a concrete application can be derived. It is therefore the personal responsibility of the individual user in all cases to check the processing and suitability of the products described in this document for the intended application in advance, and to take into consideration the legal framework and the respective state-of-the-art. We furthermore expressly draw attention to the applicability of our General Terms and Conditions.

You can find our general terms and conditions on our webpage: [www.pfleiderer.com](http://www.pfleiderer.com)