

Technical data

DecoBoard P6

Wood particleboard type P6 in accordance with EN 312, heavy-duty, for structural purposes for use in dry conditions, melamine faced on both sides.

Applications



Storage technology



Properties



Antimicrobial



Anti-slip surface



Load bearing – particularly high bending strength

Certificates



Specification			Unit	Test standard
Nominal thickness	30	38	mm	
Tolerance on thickness		±0,5	mm	EN 14323
Length- and width tolerance		± 5	mm	EN 14323
Length- and width tolerance (pre-cut panels)		± 2.5	mm	EN 14323
Flatness		≤ 2 ¹⁾	mm/m	EN 14323
Edge damage		≤ 10	mm	EN 14323
Edge damage (pre-cut panels)		≤ 3	mm	EN 14323
Surface defects (Points)		≤ 2	mm ² /m ²	EN 14323
Surface defects (Defect in the length)		≤ 20	mm/m	EN 14323
Resistance to scratching		≥ 1.5 ²⁾	N	EN 14323
Resistance to staining		≥ 3	Rating	EN 14323
Resistance to cracking		≥ 3	Rating	EN 14323
Resistance to abrasion (plain colours)		3A	Class	EN 14323
Resistance to abrasion (printed designs)		1	Class	EN 14323
Resistance to abrasion (printed designs with overlay)		3A	Class	EN 14323
Resistance to colour change in xenon arc light		min. 4 Grey Scale Grade		EN 14323
Mean density	710 - 690 ³⁾	690 - 670 ³⁾	kg/m ³	EN 323
Bending strength	15 ³⁾	14 ³⁾	N/mm ²	EN 310
Bending modulus of elasticity	2,400 ³⁾	2,200 ³⁾	N/mm ²	EN 310
Internal bond	0.35 ³⁾	0.3 ³⁾	N/mm ²	EN 319
Formaldehyde release	E1 E05			
Reaction to fire (Euroclass)	D-s2,d0 conforming to EN 13986 dependent on end use (Thickness: ≥ 9 mm / Gross density: ≥ 600 kg/m ³)			

¹⁾ If symmetrical construction

²⁾ Except smooth and matt structures, as well as decors with mother-of-pearl effect

³⁾ Core material

Technical data

DecoBoard P6

Additional information

Product standard	• EN 14322
Areas of application	• DecoBoard P6 is a urea resin-bonded wood-based panel, faced on both sides, for structural use, especially in dry conditions. It combines high load-carrying capacity and above-average durability with the advantages of an optimised facing. Ideally suitable for shelving and racking, in combination with the skidproof texture and particular product lay-up. DecoBoard P6 achieves slip resistance rating R10 and abrasion resistance class AC4 on its top face. The white coated back also improves light conditions significantly.
Core material	• PremiumBoard P6 • Wood particleboard type P6 in accordance with EN 312, heavy-duty, for structural purposes for use in dry conditions.
Product safety	• This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. • The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011. • We manufacture the panels without the use of organohalogens, heavy metals, preservatives, wood protectors or organic solvents.
Antimicrobial effect	• Surface with antimicrobial effect in 24 h for interior fit-out and finishes – Test Methodology JIS Z 2801 / ISO 22196
Resistance to heat	• Heat sources (e.g. coffee machines, printers, fax machines, etc.) should not come into direct contact with the board, otherwise cracks may form due to drying out. For continuous exposure to heat, temperatures of up to 50°C are permissible. In the case of permanent exposure to heat, we expressly draw attention to the risk of cracking.
Special	• A protective foil must be removed as soon as possible after processing – but at the latest within 6 months after delivery – to ensure residue-free removal of the foil. In addition, foiled boards must not be exposed to direct sunlight (UV radiation).
Note	• FSC certification or PEFC certification available on request. • FSC license code: FSC® C011773 • PEFC license code: PEFC/04-32-0828
Colour and surface match	• Decor, structure and core board all influence the final appearance of the end product. • Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. • The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. • To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2025 Pfleiderer Deutschland GmbH

This information is issued with great care. We do not however accept any responsibility for the accuracy, completeness and timeliness. There may be slight colour differences between the printed brochure image and the actual design.

Due to the continuous development and modification of our products, possible changes to the relevant standards, laws and regulations, our technical data sheets and product documents expressly do not represent a legally binding guarantee of the properties specified therein. In particular, no suitability for a specific purpose can be derived from this information. It is therefore the personal responsibility of the individual user to check the processing and suitability of the products described in this document for the intended use and to take into account the legal framework and the current state of the art. Furthermore, we expressly refer to the validity of our general terms and conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com

Pfleiderer Deutschland GmbH

Ingolstädter Str. 51
92318 Neumarkt
Germany

phone +49 (0) 91 81 28 48 0
Fax +49 (0) 91 81 28 48 2
info@pfleiderer.com
www.pfleiderer.com