


## Technical data

### Duropal Element Birch Multiplex

Birch veneer panel, glued moisture-resistant, surfaced on both sides with Duropal HPL. This HPL bonded board guarantees high bending strength.



#### Applications



Furniture and interior fitting

#### Properties



Variety of decors and / or textures



Easy care



Antimicrobial



Food harmless



Load bearing – particularly high bending strength

#### Certificates



Specification			Unit	Test standard
Nominal thickness	19.6	28.6	mm	
HPL-thickness	0.8	0.8	mm	
Design front edge	not processed			
Design rear edge	not processed			
Tolerance on thickness	± 0.5		mm	ISO 13894-1
Tolerance on length	± 5		mm	ISO 13894-1
Tolerance on width	± 5		mm	ISO 13894-1
Surface defects – HPL	max. 1 <sup>1)</sup> max. 10 <sup>2)</sup>		mm <sup>2</sup> /m <sup>2</sup> mm/m <sup>2</sup>	EN 438-2
Straightness of edges	± 0.5		mm/m	ISO 13894-1
Squareness	≤ 2		mm/m	ISO 13894-1
Flatness (length)	max. 2		mm/m	ISO 13894-1
Flatness (width)	max. 2		mm/m	ISO 13894-1
Resistance to wet heat, 100 °C (other finishes) – HPL	min. 4		rating	EN 438-2
Resistance to dry heat, 160 °C (other finishes) – HPL	min. 4		rating	EN 438-2
Resistance to water vapour (other finishes) – HPL	min. 4		rating	EN 438-2
Resistance to surface wear – HPL	min. 150		cycles	EN 438-2
Resistance to scratching (textured finishes) – HPL	min. 3		rating	EN 438-2
Resistance to impact (small diameter ball)	min. 15		N	ISO 13894-1
Stain resistance (groups 1 & 2) – HPL	min. 5		rating	EN 438-2
Stain resistance (group 3) – HPL	min. 4		rating	EN 438-2
Resistance to colour change (xenon arc light) – HPL	4 to 5 Grey Scale Grade			EN 438-2
Reaction to fire	normally flammable			

## Technical data

### Duropal Element Birch Multiplex

Specification			Unit	Test standard
Nominal thickness	19.6	28.6	mm	
HPL-thickness	0.8	0.8	mm	
Reaction to fire (Euroclass)	D-s2,d0			EN 13501-1, CWFT conforming to 2003/593/EG
Formaldehyde emission class	E1 E05			EN 717-1
Mean density	720 <sup>3)</sup>		kg/m <sup>3</sup>	EN 323
Bending strength	≥ 60 <sup>3)</sup>	≥ 40 <sup>3)</sup>	N/mm <sup>2</sup>	EN 310
Modulus of elasticity (bending stiffness)	≥ 6,000 <sup>3)</sup>		N/mm <sup>2</sup> kg/cm <sup>2</sup>	EN 310
Internal bond	≥ 0.8 <sup>3)</sup>		kg/cm <sup>2</sup> N/mm <sup>2</sup>	EN 319
Resistance to fixings (face)	≥ 2,000		N	ISO 13894-1
Resistance to fixings (edge)	≥ 2,000		N	ISO 13894-1
Bonding strength	≥ 1.7		N/mm <sup>2</sup>	ISO 13894-1
Flexural tensile strength	≥ 1.7		N/mm <sup>2</sup>	ISO 13894-1
Durability – Glue-line quality	5		rating	ISO 13894-1
Durability – Resistance to elevated temperature	no effect			ISO 13894-1

<sup>1)</sup> Dirt, spots and similar surface defects

<sup>2)</sup> Fibres, hairs and scratches

<sup>3)</sup> Core material

#### Additional information

Product standard	<ul style="list-style-type: none"> <li>in accordance with EN 13894-1</li> </ul>
Areas of application	<ul style="list-style-type: none"> <li>High quality furniture and installations on which high static demands are made: Shop fitting, discerning interior design, library, shop and chemist fitting and in the office furniture sector.</li> </ul>
Core material	<ul style="list-style-type: none"> <li>PremiumBoard Birch Multiplex</li> <li>Extremely stable veneer panel with attractive narrow edge for indoor elements and furniture.</li> </ul>
Product safety	<ul style="list-style-type: none"> <li>This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered.</li> <li>The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011.</li> <li>The decorative surface and the core consists of paper layers, which are impregnated with thermosetting resins. The resins harden completely during the manufacturing process by heat and high-pressure. They form a stable, resistant and non-reactive material.</li> <li>We manufacture the panels without the use of organohalogens, heavy metals, preservatives, wood protectors or organic solvents.</li> </ul>

## Technical data

### Duropal Element Birch Multiplex

Antimicrobial effect	<ul style="list-style-type: none"> <li>• Surface with antimicrobial effect in 24 h for interior fit-out and finishes – Test Methodology JIS Z 2801 / ISO 22196</li> </ul>
Special	<ul style="list-style-type: none"> <li>• The coarser the structure and the lighter the decor, the greater the scratch resistance.</li> <li>• Depending on the decor and surface texture, slightly different surface visual impressions can result between cut panels viewed from different angles. This is a result of the production methods and does not constitute a quality defect.</li> <li>• Especially for large applications, we recommend paying attention to the colour and texture uniformity of the boards and cut products used when further processing and installing and that the production direction is taken into account.</li> <li>• With intensive plain decors, especially in the red range, colour pigment wash-out may occur under certain circumstances. It is possible that colour pigments are not bound by the resin during the impregnation of the decor paper and are only deposited on the surface of the impregnate and are thus directly on the surface. If cleaning is then carried out, slight discolouration of the cleaning cloths can be observed. This is particularly the case when solvent-based cleaners are used. This is not a product defect.</li> <li>• By some decor/texture combinations a slight surface disruption may be visible. This is due to the construction of the core material and is not indicative of a quality fault.</li> <li>• Classification HGP / HGS / HGF is achieved with the surface textures recommended for horizontal applications. Requirements of classification VGP / VGS / VGF are met by all surface textures. Please refer to our sales documentation, to check which textures are available for this product.</li> </ul>
Note	<ul style="list-style-type: none"> <li>• FSC-certification available on request.</li> <li>• FSC license code: FSC® C011773</li> </ul>
Colour and surface match	<ul style="list-style-type: none"> <li>• Decor, structure and core board all influence the final appearance of the end product.</li> <li>• Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect.</li> <li>• The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors.</li> <li>• To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.</li> </ul>

Further information on products, formats and decor/structure combinations is available at [www.pfleiderer.com](http://www.pfleiderer.com)

© Copyright 2025 Pfleiderer Deutschland GmbH

This information is issued with great care. We do not however accept any responsibility for the accuracy, completeness and timeliness. There may be slight colour differences between the printed brochure image and the actual design.

Due to the continuous development and modification of our products, possible changes to the relevant standards, laws and regulations, our technical data sheets and product documents expressly do not represent a legally binding guarantee of the properties specified therein. In particular, no suitability for a specific purpose can be derived from this information. It is therefore the personal responsibility of the individual user to check the processing and suitability of the products described in this document for the intended use and to take into account the legal framework and the current state of the art. Furthermore, we expressly refer to the validity of our general terms and conditions.

You can find our general terms and conditions on our webpage: [www.pfleiderer.com](http://www.pfleiderer.com)

#### Pfleiderer Deutschland GmbH

Ingolstädter Str. 51  
92318 Neumarkt  
Germany

phone +49 (0) 91 81 28 48 0  
Fax +49 (0) 91 81 28 48 2  
[info@pfleiderer.com](mailto:info@pfleiderer.com)  
[www.pfleiderer.com](http://www.pfleiderer.com)