



Technical data

Duropal Element SolidColor XTreme MDF plus

HPL bonded board consisting of a medium-density fibreboard (MDF) with uniform structure, surfaced on both sides with Duropal SolidColor XTreme, a decor-identical through-coloured laminate core and an attractive supermatt surface material with an anti-fingerprint effect.



Applications



Furniture and interior fitting

Properties



Easy care



Anti-fingerprint



Food harmless

Certificates



Specification			Unit	Test standard
Nominal thickness	17.6	20.6	mm	
HPL-thickness	0.8	0.8	mm	
Design front edge	not processed			
Design rear edge	not processed			
Tolerance on thickness	± 0.5		mm	ISO 13894-1
Tolerance on length	± 5		mm	ISO 13894-1
Tolerance on width	± 5		mm	ISO 13894-1
Surface defects – HPL	max. 1 ¹⁾ max. 10 ²⁾		mm ² /m ² mm/m ²	EN 438-2
Straightness of edges	± 0.5		mm/m	ISO 13894-1
Squareness	≤ 2		mm/m	ISO 13894-1
Flatness (length)	max. 2		mm/m	ISO 13894-1
Flatness (width)	max. 2		mm/m	ISO 13894-1
Resistance to dry heat, 160 °C (other finishes) – HPL	min. 4		rating	EN 438-2
Resistance to water vapour (other finishes) – HPL	min. 4		rating	EN 438-2
Resistance to surface wear – HPL	min. 150		cycles	EN 438-2
Resistance to scratching (smooth finishes) – HPL	min. 3		rating	EN 438-2
Stain resistance (groups 1 & 2) – HPL	min. 5		rating	EN 438-2
Stain resistance (group 3) – HPL	min. 4		rating	EN 438-2
Resistance to colour change (xenon arc light) – HPL	min. 4 Grey Scale Grade ³⁾ min. 3 Grey Scale Grade ⁴⁾			EN 438-2
Reaction to fire	normally flammable			
Reaction to fire (Euroclass)	D-s2,d0			EN 13501-1, CWFT conforming to 2003/593/EG
Formaldehyde emission class	E1 E05 TSCA Title VI			EN 717-1

Technical data

Duropal Element SolidColor XTreme MDF plus

Specification			Unit	Test standard
Nominal thickness	17.6	20.6	mm	
HPL-thickness	0.8	0.8	mm	
Mean density	710 ⁵⁾		kg/m ³	EN 323
Bending strength	23 ⁵⁾		N/mm ²	EN 310
Modulus of elasticity (bending stiffness)	2,100 ⁵⁾		N/mm ²	EN 310
Internal bond	0.45 ⁵⁾		N/mm ²	EN 319
Resistance to fixings (face)	≥ 1,500		N	ISO 13894-1
Resistance to fixings (edge)	≥ 500		N	ISO 13894-1
Bonding strength	≥ 0.8		N/mm ²	ISO 13894-1
Flexural tensile strength	≥ 0.8		N/mm ²	ISO 13894-1
Durability – Glue-line quality	≥ 3		rating	ISO 13894-1
Durability – Resistance to elevated temperature	no effect			ISO 13894-1

1) Dirt, spots and similar surface defects

2) Fibres, hairs and scratches

3) Texture

4) Core layers

5) Core material

Additional information

Product standard	in accordance with EN 13894-2
Areas of application	The special material composition opens up new possibilities for discerning furniture and interior design concepts. In the private sector, but also in restaurants, in cultural and conference centres, banks, offices and in shop design. For installations, design and presentation elements, shelving, furniture fronts, racking, desks, tabletops and worktops, etc. However, the material is not suitable for areas that are subject to major climatic fluctuations in terms of temperature and humidity or that are subject to permanent exposure to moisture.
Core material	- StyleBoard MDF plus - Medium-density fibreboard (MDF), with a uniform structure.

Technical data

Duropal Element SolidColor XTreme MDF plus

Product safety	- This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. - The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011.
Special	- The smoother the structure and the the darker the decor, the more sensitive it is to stains. - Due to a low orientation of the lacquered surface the field of application, the conditions of lighting and the decor may cause certain optical effects. This is a result of the production methods and does not constitute a quality defect. - Depending on the decor and surface texture, slightly different surface visual impressions can result between cut panels viewed from different angles. This is a result of the production methods and does not constitute a quality defect. - Especially for large applications, we recommend paying attention to the colour and texture uniformity of the boards and cut products used when further processing and installing and that the production direction is taken into account. - To avoid any possible aesthetic and optical impairments, the orientation of the boards specified on the protection film of the product must strictly be followed, especially for large-surface applications. - XTreme Semi Matt doesn't prevent scratches, but allows horizontal application! - Please note that due to their material composition, through-dyed laminates are somewhat harder and more brittle than classic laminates with dark phenol resin core and are subject to marked warp in the event of climate fluctuations. - Due to the through-dyed core of the material, slight colour variations to other products cannot be avoided.
Note	- FSC certification or PEFC certification available on request. - FSC license code: FSC® C011773 - PEFC license code: PEFC/04-32-0828
Colour and surface match	- Decor, structure and core board all influence the final appearance of the end product. - Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. - The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. - To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2025 Pfleiderer Deutschland GmbH

This information is issued with great care. We do not however accept any responsibility for the accuracy, completeness and timeliness. There may be slight colour differences between the printed brochure image and the actual design.

Due to the continuous development and modification of our products, possible changes to the relevant standards, laws and regulations, our technical data sheets and product documents expressly do not represent a legally binding guarantee of the properties specified therein. In particular, no suitability for a specific purpose can be derived from this information. It is therefore the personal responsibility of the individual user to check the processing and suitability of the products described in this document for the intended use and to take into account the legal framework and the current state of the art. Furthermore, we expressly refer to the validity of our general terms and conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com

Pfleiderer Deutschland GmbH

Ingolstädter Str. 51
92318 Neumarkt
Germany

phone +49 (0) 91 81 28 48 0
Fax +49 (0) 91 81 28 48 2
info@pfleiderer.com
www.pfleiderer.com