


November 2025


Technical data

Duropal Element XTreme plus MDF plus

HPL bonded board consisting of a medium-density fibreboard (MDF) with uniform structure, surfaced on both sides with Duropal HPL XTreme plus, an attractive supermatt surface material with an anti-fingerprint effect, which is ideal for horizontal, heavily used surfaces.



Applications



Properties



Easy care



Anti-fingerprint



Antimicrobial



Food harmless



High scratch resistance

Certificates





Specification			Unit	Test standard
Nominal thickness	17.6	20.6	mm	
HPL-thickness	0.8	0.8	mm	
Design front edge	not processed			
Design rear edge	not processed			
Tolerance on thickness	± 0.5		mm	ISO 13894-1
Tolerance on length	± 5		mm	ISO 13894-1
Tolerance on width	± 5		mm	ISO 13894-1
Surface defects – HPL	max. 1 ¹⁾ max. 10 ²⁾		mm²/m² mm/m²	EN 438-2
Straightness of edges	± 0.5		mm/m	ISO 13894-1
Squareness	≤2		mm/m	ISO 13894-1
Flatness (length)	max. 2		mm/m	ISO 13894-1
Flatness (width)	max. 2		mm/m	ISO 13894-1
Resistance to wet heat, 100 °C (other finishes) – HPL	min. 4		rating	EN 438-2
Resistance to dry heat, 160 °C (other finishes) – HPL	min. 4		rating	EN 438-2
Resistance to surface wear – HPL	min. 400		cycles	EN 438-2
Resistance to scratching (smooth finishes) – HPL	min. 4		rating	EN 438-2
Resistance to impact (small di- ameter ball)	min. 15		N	ISO 13894-1
Stain resistance (groups 1 & 2) – HPL	min. 5		rating	EN 438-2
Stain resistance (group 3) – HPL	min. 5		rating	EN 438-2
Resistance to colour change (xenon arc light) – HPL	4 to 5 Grey Scale Grade		•	EN 438-2
Reaction to fire	normally flammable			



November 2025

Technical data

Duropal Element XTreme plus MDF plus

Specification			Unit	Test standard
Nominal thickness	17.6	20.6	mm	
HPL-thickness	0.8	0.8	mm	
Reaction to fire (Euroclass)	D-s2,d0			EN 13501-1, CWFT conforming to 2003/593/EG
Formaldehyde emission class	E1 E05 TSCA Title VI			EN 717-1
Mean density	710 ³⁾		kg/m³	EN 323
Bending strength	23 3)		N/mm²	EN 310
Modulus of elasticity (bending stiffness)	2,100 ³⁾		N/mm²	EN 310
Internal bond	0.45 3)		N/mm²	EN 319
Resistance to fixings (face)	≥ 1,500		N	ISO 13894-1
Resistance to fixings (edge)	<u> </u>		N	ISO 13894-1
Bonding strength	≥ 0.8		N/mm²	ISO 13894-1
Flexural tensile strength	≥ 0.8		N/mm²	ISO 13894-1
Durability – Glue-line quality	≥3		rating	ISO 13894-1
Durability – Resistance to elevated temperature	no effect			ISO 13894-1

Dirt, spots and similar surface defects
 Fibres, hairs and scratches

Additional information

Product standard	• in accordance with EN 13894-2
Areas of application	 Decorative, sturdy elements for furniture and interior design where a uniform core material with very high edge quality – for profiling and lacquering – is required: e. g. in restaurants and shop fitting and for office and interior furniture.
Core material	StyleBoard MDF plusMedium-density fibreboard (MDF), with a uniform structure.
Product safety	 This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011.

³⁾ Core material



November 2025

Technical data

Duropal Element XTreme plus MDF plus

Antimicrobial effect	Surface with antimicrobial effect in 24 h for interior fit-out and finishes – Test Methodology JIS Z 2801 / ISO 22196
Special	 The smoother the structure and the the darker the decor, the more sensitive it is to stains. Due to a low orientation of the lacquered surface the field of application, the conditions of lighting and the decor may cause certain optical effects. This is a result of the production methods and does not constitute a quality defect. Depending on the decor and surface texture, slightly different surface visual impressions can result between cut panels viewed from different angles. This is a result of the production methods and does not constitute a quality defect. Especially for large applications, we recommend paying attention to the colour and texture uniformity of the boards and cut products used when further processing and installing and that the production direction is taken into account. To avoid any possible aesthetic and optical impairments, the orientation of the boards specified on the protection film of the product must strictly be followed, especially for large-surface applications. XTreme plus doesn't prevent scratches, but allows horizontal application! Classification HGP / HGS / HGF is achieved with the surface textures recommended for horizontal applications. Requirements of classification VGP / VGS / VGF are met by all surface textures. Please refer to our sales documentation, to check which textures are available for this product.
Note	FSC certification or PEFC certification available on request. FSC license code: FSC® C011773 PEFC license code: PEFC/04-32-0828
Colour and surface match	 Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2025 Pfleiderer Deutschland GmbH

This information is issued with great care. We do not however accept any responsibility for the accuracy, completeness and timeliness. There may be slight colour differences between the printed brochure image and the actual design.

Due to the continuous development and modification of our products, possible changes to the relevant standards, laws and regulations, our technical data sheets and product documents expressly do not represent a legally binding guarantee of the properties specified therein. In particular, no suitability for a specific purpose can be derived from this information. It is therefore the personal responsibility of the individual user to check the processing and suitability of the products described in this document for the intended use and to take into account the legal framework and the current state of the art. Furthermore, we expressly refer to the validity of our general terms and conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com