



Technical data

Duropal Element XTreme plus P2

HPL bonded board consisting of a particleboard type P2 conforming to EN 312, surfaced on both sides with Duropal HPL XTreme plus, an attractive supermatt surface material with an anti-fingerprint effect, which is ideal for horizontal, heavily used surfaces.



Applications



Furniture and interior fitting

Properties



Easy care



Anti-fingerprint



Antimicrobial



Food harmless



High scratch resistance



Particularly low emission

Certificates



Specification									Unit	Test standard
Nominal thickness	9.6	16	17.6	19	20.6	25	29.6	39.6	mm	
HPL-thickness	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	mm	
Design front edge	not processed									
Design rear edge	not processed									
Tolerance on thickness	± 0.5								mm	ISO 13894-1
Tolerance on length	± 5								mm	ISO 13894-1
Tolerance on width	± 5								mm	ISO 13894-1
Surface defects – HPL	max. 1 ¹⁾ max. 10 ²⁾								mm ² /m ² mm/m ²	EN 438-2
Straightness of edges	± 0.5								mm/m	ISO 13894-1
Squareness	≤ 2								mm/m	ISO 13894-1
Flatness (length)	-	max. 2	max. 2	max. 2	max. 2	max. 2	max. 2	max. 2	mm/m	ISO 13894-1
Flatness (width)	-	max. 2	max. 2	max. 2	max. 2	max. 2	max. 2	max. 2	mm/m	ISO 13894-1
Resistance to wet heat, 100 °C (other finishes) – HPL	min. 4								rating	EN 438-2
Resistance to dry heat, 160 °C (other finishes) – HPL	min. 4								rating	EN 438-2
Resistance to surface wear – HPL	min. 400								cycles	EN 438-2
Resistance to scratching (smooth finishes) – HPL	min. 4								rating	EN 438-2
Resistance to impact (small diameter ball)	min. 15								N	ISO 13894-1
Stain resistance (groups 1 & 2) – HPL	min. 5								rating	EN 438-2
Stain resistance (group 3) – HPL	min. 5								rating	EN 438-2
Resistance to colour change (xenon arc light) – HPL	4 to 5 Grey Scale Grade									EN 438-2
Reaction to fire	normally flammable									

Technical data

Duropol Element XTreme plus P2

Specification									Unit	Test standard
Nominal thickness	9.6	16	17.6	19	20.6	25	29.6	39.6	mm	
HPL-thickness	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	mm	
Reaction to fire (Euroclass)	not classified	D-s2,d0	D-s2,d0	D-s2,d0	D-s2,d0	D-s2,d0	not classified	not classified		EN 13501-1, CWFT conforming to 2003/593/EG
Formaldehyde emission class	E1 E05 TSCA Title VI									EN 717-1
Mean density	≥ 720 ³⁾	670 - 650 ³⁾	670 - 650 ³⁾	670 - 650 ³⁾	670 - 650 ³⁾	630 - 610 ³⁾	600 - 580 ³⁾	580 - 540 ³⁾	kg/m ³	EN 323
Bending strength	11 ³⁾	11 ³⁾	11 ³⁾	11 ³⁾	11 ³⁾	10.5 ³⁾	9.5 ³⁾	8.5 ³⁾	N/mm ²	EN 310
Modulus of elasticity (bending stiffness)	1,800 ³⁾	1,600 ³⁾	1,600 ³⁾	1,600 ³⁾	1,600 ³⁾	1,500 ³⁾	1,350 ³⁾	1,200 ³⁾	N/mm ²	EN 310
Internal bond	0.4 ³⁾	0.35 ³⁾	0.35 ³⁾	0.35 ³⁾	0.35 ³⁾	0.3 ³⁾	0.25 ³⁾	0.2 ³⁾	N/mm ²	EN 319
Resistance to fixings (face)	≥ 40	≥ 600	≥ 600	≥ 600	≥ 600	≥ 600	≥ 600	≥ 600	N/mm N	ISO 13894-1
Resistance to fixings (edge)	-	≥ 350	≥ 350	≥ 350	≥ 350	≥ 350	≥ 350	≥ 350	N	ISO 13894-1
Bonding strength	≥ 0.6								N/mm ²	ISO 13894-1
Flexural tensile strength	≥ 0.6								N/mm ²	ISO 13894-1
Durability – Glue-line quality	≥ 3								rating	ISO 13894-1
Durability – Resistance to elevated temperature	no effect									ISO 13894-1

¹⁾ Dirt, spots and similar surface defects

²⁾ Fibres, hairs and scratches

³⁾ Core material

Additional information

Product standard	in accordance with EN 13894-2
Areas of application	Furniture production and interior design wherever high demands are made on quality and durability: For kitchen and interior design furniture, in shop fitting and partition wall construction, for interior fitting of banks, offices, schools, clinics, laboratories, retail buildings, in shipbuilding and motor vehicle construction.
Core material	- ClassicBoard P2 - Urea resin-bonded particleboard, type P2 conforming to EN 312, suitable for non load-bearing purposes in dry areas.
Product safety	- This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. - The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011. - We manufacture the panels without the use of organohalogens, heavy metals, preservatives, wood protectors or organic solvents.

Technical data

Duropol Element XTreme plus P2

Antimicrobial effect	Surface with antimicrobial effect in 24 h for interior fit-out and finishes – Test Methodology JIS Z 2801 / ISO 22196
Special	- The smoother the structure and the the darker the decor, the more sensitive it is to stains. - Due to a low orientation of the lacquered surface the field of application, the conditions of lighting and the decor may cause certain optical effects. This is a result of the production methods and does not constitute a quality defect. - Depending on the decor and surface texture, slightly different surface visual impressions can result between cut panels viewed from different angles. This is a result of the production methods and does not constitute a quality defect. - Especially for large applications, we recommend paying attention to the colour and texture uniformity of the boards and cut products used when further processing and installing and that the production direction is taken into account. - To avoid any possible aesthetic and optical impairments, the orientation of the boards specified on the protection film of the product must strictly be followed, especially for large-surface applications. - XTreme plus doesn't prevent scratches, but allows horizontal application! - Classification HGP / HGS / HGF is achieved with the surface textures recommended for horizontal applications. Requirements of classification VGP / VGS / VGF are met by all surface textures. Please refer to our sales documentation, to check which textures are available for this product.
Note	- FSC certification or PEFC certification available on request. - FSC license code: FSC® C011773 - PEFC license code: PEFC/04-32-0828
Colour and surface match	- Decor, structure and core board all influence the final appearance of the end product. - Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. - The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. - To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2025 Pfleiderer Deutschland GmbH

This information is issued with great care. We do not however accept any responsibility for the accuracy, completeness and timeliness. There may be slight colour differences between the printed brochure image and the actual design.

Due to the continuous development and modification of our products, possible changes to the relevant standards, laws and regulations, our technical data sheets and product documents expressly do not represent a legally binding guarantee of the properties specified therein. In particular, no suitability for a specific purpose can be derived from this information. It is therefore the personal responsibility of the individual user to check the processing and suitability of the products described in this document for the intended use and to take into account the legal framework and the current state of the art. Furthermore, we expressly refer to the validity of our general terms and conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com