

January 2023


Technical data

Duropal Element XTreme Touch P2

Flat bonded element consisting of a particleboard type P2 to EN 312, surfaced on both sides with Duropal XTreme Touch, an attractive supermatt surface material with an anti-fingerprint effect in combination with natural-looking stone or wood structure.



Applications



Properties



Certificates









Specification									Unit	Test standard
Nominal thickness	9.6	16	17.6	19	20.6	25	29.6	39.6	mm	
HPL-thickness	0.8	0.8	0.8	0.8	0.8	0.8	0.8	8.0	mm	
Design front edge		<u> </u>		not pro	cessed					
Design rear edge		not processed								
Tolerance on thickness				±	0.5				mm	ISO 13894-1
Tolerance on length		± 5					mm	ISO 13894-1		
Tolerance on width		± 5						mm	ISO 13894-1	
Surface defects – HPL	max. 1 ¹⁾ max. 10 ²⁾						mm²/m² mm/m²	EN 438-2		
Straightness of edges	± 0.5							mm/m	ISO 13894-1	
Squareness	≤2						mm/m	ISO 13894-1		
Flatness (length)	≤2						mm/m	ISO 13894-1		
Flatness (width)	≤2						mm/m	ISO 13894-1		
Resistance to wet heat, 100 °C (other finishes) – HPL	min. 4						rating	EN 438-2		
Resistance to dry heat, 160 °C (other finishes) – HPL	min. 4					rating	EN 438-2			
Resistance to water vapour (oth- er finishes) – HPL	min. 4						rating	EN 438-2		
Resistance to surface wear – HPL	min. 150						cycles	EN 438-2		
Resistance to scratching (tex- tured finishes) – HPL	min. 3					rating	EN 438-2			
Resistance to impact (small diameter ball)	min. 15 ³⁾					N	ISO 13894-1			
Stain resistance (groups 1 & 2) – HPL	min. 5					rating	EN 438-2			
Stain resistance (group 3) – HPL	min. 4					rating	EN 438-2			



January 2023

Technical data

Duropal Element XTreme Touch P2

Specification									Unit	Test standard
Nominal thickness	9.6	16	17.6	19	20.6	25	29.6	39.6	mm	
HPL-thickness	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	mm	
Resistance to colour change (xenon arc light) – HPL		4 to 5 Grey Scale Grade								EN 438-2
Reaction to fire		normally flammable								
Reaction to fire (Euroclass)	not classi- fied	D- s2,d0	D- s2,d0	D- s2,d0	D- s2,d0	D- s2,d0	not classi- fied	not classi- fied		EN 13501-1, CWFT acc. to 2003/593/ EG
Formaldehyde emission class	n class E1 E05								EN 717-1	
Mean density	≥ 720 ⁴⁾	640 ⁴⁾	640 ⁴⁾	640 ⁴⁾	640 ⁴⁾	620 ⁴⁾	600 ⁴⁾	580 ⁴⁾	kg/m³	EN 323
Bending strength	11 ⁴⁾	11 ⁴⁾	11 ⁴⁾	11 ⁴⁾	11 ⁴⁾	10.5 ⁴⁾	9.5 ⁴⁾	8.5 ⁴⁾	N/mm²	EN 310
Modulus of elasticity (bending stiffness)	1,800 ⁴⁾	1,600 ⁴⁾		1,600 ⁴⁾	1,600 ⁴⁾	1,500 ⁴⁾	1,350 ⁴⁾	1,200 4)	N/mm²	EN 310
Internal bond	0.4 4)	0.35 ⁴⁾	0.35 ⁴⁾	0.35 ⁴⁾	0.35 ⁴⁾	0.3 ⁴⁾	0.25 ⁴⁾	0.2 4)	N/mm²	EN 319
Surface soundness	0.8 ⁴⁾							N/mm²	EN 311	
Durability – Water resistance	≤ 15							%	ISO 13894-1	
Resistance to fixings (face)	≥ 50	≥ 600	≥ 600	≥ 600	≥ 600	≥ 600	≥ 600	≥ 600	N/mm N	ISO 13894-1
Resistance to fixings (edge)		≥ 500	≥ 500	≥ 500	≥ 500	≥ 500	≥ 500	≥ 500	N	ISO 13894-1
Bonding strength	≥ 0.6							N/mm²	ISO 13894-1	
Flexural tensile strength	≥ 0.6							N/mm²	ISO 13894-1	
Durability – Glue-line quality	≥3						rating	ISO 13894-1		
Durability – Resistance to elevated temperature	no effect								ISO 13894-1	

Dirt, spots and similar surface defectsFibres, hairs and scratches

Additional information

Product standard	• EN 13894-1
Areas of application	 Furniture production and interior design wherever high demands are made on quality and durability: For kitchen and interior design furniture, in shop fitting and partition wall construction, for interior fitting of banks, offices, schools, clinics, laboratories, retail buildings, in shipbuilding and motor vehicle construction.
Core material	 ClassicBoard P2 CARB2 Low emission particleboard core, type P2 in accordance with EN 312, suitable for non load-bearing purposes in dry areas.

³⁾ No surface damage according to the standard; optical change of the surface (>10 N) possible

⁴⁾ Core material



January 2023

Technical data

Duropal Element XTreme Touch P2

	This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered.
Product safety	 The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011.
	 We manufacture the panels without the use of halogens, heavy metals, preservatives, wood protectors or organic solvents.
Special	 The coarser the structure and the lighter the decor, the greater the scratch resistance. Due to a low orientation of the electron beam cured surface the field of application, the conditions of space lighting and the décor may cause certain optical effects. This is a result of the production methods and does not constitute a quality defect.
	 Depending on the decor and surface texture, slightly different surface visual impressions can result between cut panels viewed from different angles. This is a result of the production methods and does not constitute a quality defect.
	 Especially for large applications, we recommend paying attention to the colour and texture uniformity of the boards and cut products used when further processing and installing and that the production direction is taken into account.
	 To avoid any possible aesthetic and optical impairments, the orientation of the boards specified on the protection film of the product must strictly be followed, especially for large-surface applications. Duropal XTreme Touch doesn't prevent scratches, but allows horizontal application!
Note	FSC certification or PEFC certification available on request.
Note	 FSC license code: FSC[®] C011773 PEFC license code: PEFC/04-32-0828
Colour and surface match	 Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect.
	 The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2023 Pfleiderer Deutschland GmbH

This information has been compiled with the greatest care. Nevertheless we can assume no liability for the correctness, completeness and up-to-dateness of this information. Colour deviations caused by the printing technology are possible. In view of the ongoing further development and adaptation of our products, possible amendments to the relevant standards, laws and regulations, our technical data sheets and product documentation expressly do not constitute a legally binding assurance of the properties described there. In particular no guarantee of suitability for a concrete application can be derived. It is therefore the personal responsibility of the individual user in all cases to check the processing and suitability of the products described in this document for the intended application in advance, and to take into consideration the legal framework and the respective state-of-the-art. We furthermore expressly draw attention to the applicability of our General Terms and Conditions.