



Technical data

Duropal HPL Compact LabSpec, black core

Compact high-pressure laminate in standard quality conforming to EN 438-4:CGS, suitable for laboratory facilities. With uniform black-coloured core and decorative, chemical-resistant lacquered surface on both sides (SEFA 3 class).



Applications



Furniture and interior fitting

Properties



Easy care



Resistant to chemicals



Low swelling / moisture resistant



High impact resistance

Certificates



Specification									Unit	Test standard
Nominal thickness	2	3	4	5	6	8	10	12	mm	
Tolerance on thickness	± 0.2	± 0.3	± 0.3	± 0.4	± 0.4	± 0.5	± 0.5	± 0.6	mm	EN 438-2
Tolerance on length	+ 10								mm	EN 438-2
Tolerance on width	+ 10								mm	EN 438-2
Surface defects	max. 1 ¹⁾ max. 10 ²⁾								mm ² /m ² mm/m ²	EN 438-2
Edge defects	max. 3								mm	EN 438-2
Straightness of edges	max. 1.5								mm/m	EN 438-2
Squareness	max. 1.5								mm/m	EN 438-2
Flatness	max. 8	max. 8	max. 8	max. 8	max. 5	max. 5	max. 3	max. 3	mm/m	EN 438-2
Density	min. 1,350								kg/m ³	EN ISO 1183-1
Bending strength	min. 80								MPa	EN ISO 178
Flexural modulus	min. 9,000								MPa	EN ISO 178
Resistance to crazing	min. 4								rating	EN 438-2
Dimensional stability at elevated temperature (length)	max. 0.4	max. 0.4	max. 0.4	max. 0.3	max. 0.3	max. 0.3	max. 0.3	max. 0.3	%	EN 438-2
Dimensional stability at elevated temperature (width)	max. 0.8	max. 0.8	max. 0.8	max. 0.6	max. 0.6	max. 0.6	max. 0.6	max. 0.6	%	EN 438-2
Resistance to wet heat, 100 °C (other finishes)	min. 4								rating	EN 438-2
Resistance to dry heat, 160 °C (other finishes)	min. 4								rating	EN 438-2
Resistance to water vapour (other finishes)	min. 4								rating	EN 438-2
Resistance to immersion in boiling water (other finishes)	min. 4								rating	EN 438-2
Resistance to immersion in boiling water (edge)	min. 3								rating	EN 438-2

Technical data

Duropal HPL Compact LabSpec, black core

Specification									Unit	Test standard
Nominal thickness	2	3	4	5	6	8	10	12	mm	
Resistance to immersion in boiling water	max. 5 ³⁾ max. 6 ⁴⁾	max. 5 ³⁾ max. 6 ⁴⁾	max. 5 ³⁾ max. 6 ⁴⁾	max. 2 ^{3) 4)}	max. 2 ^{3) 4)}	max. 2 ^{3) 4)}	max. 2 ^{3) 4)}	max. 2 ^{3) 4)}	%	EN 438-2
Resistance to surface wear	min. 150								cycles	EN 438-2
Resistance to scratching (textured finishes)	min. 3								rating	EN 438-2
Resistance to impact by large diameter ball – impression diameter	max. 10								mm	EN 438-2
Resistance to impact by large diameter ball – Fall height	min. 1,400	min. 1,400	min. 1,400	min. 1,400	min. 1,800	min. 1,800	min. 1,800	min. 1,800	mm	EN 438-2
Chemical resistance (SEFA 3 – Method A & B)	passed									SEFA 3:2020
Stain resistance (groups 1 & 2)	5								rating	EN 438-2
Stain resistance (group 3)	5								rating	EN 438-2
Resistance to colour change (xenon arc light)	4 to 5 Grey Scale Grade									EN 438-2
Reaction to fire	normally flammable									
Reaction to fire (Euroclass)	not classified	not classified	not classified	not classified	D-s2,d0	D-s2,d0	D-s2,d0	D-s2,d0		EN 13501-1, CWFT conforming to 2003/593/EG
Formaldehyde emission class	E1 E05									EN 717-1

¹⁾ Dirt, spots and similar surface defects

²⁾ Fibres, hairs and scratches

³⁾ Mass increase

⁴⁾ Thickness increase

Specification								Unit	Test standard
Nominal thickness	13	15	16	17	18	19	20	mm	
Tolerance on thickness	± 0.6	± 0.6	± 0.7	± 0.7	± 0.7	± 0.7	± 0.8	mm	EN 438-2
Tolerance on length	+ 10							mm	EN 438-2
Tolerance on width	+ 10							mm	EN 438-2
Surface defects	max. 1 ¹⁾ max. 10 ²⁾							mm ² /m ² mm/m ²	EN 438-2
Edge defects	max. 3							mm	EN 438-2
Straightness of edges	max. 1.5							mm/m	EN 438-2
Squareness	max. 1.5							mm/m	EN 438-2
Flatness	max. 3							mm/m	EN 438-2
Density	min. 1,350							kg/m ³	EN ISO 1183-1
Bending strength	min. 80							MPa	EN ISO 178
Flexural modulus	min. 9,000							MPa	EN ISO 178
Resistance to crazing	min. 4							rating	EN 438-2
Dimensional stability at elevated temperature (length)	max. 0.3							%	EN 438-2
Dimensional stability at elevated temperature (width)	max. 0.6							%	EN 438-2
Resistance to wet heat, 100 °C (other finishes)	min. 4							rating	EN 438-2
Resistance to dry heat, 160 °C (other finishes)	min. 4							rating	EN 438-2

Technical data

Duropal HPL Compact LabSpec, black core

Specification	13	15	16	17	18	19	20	Unit	Test standard
Nominal thickness								mm	
Resistance to water vapour (other finishes)				min. 4				rating	EN 438-2
Resistance to immersion in boiling water (other finishes)				min. 4				rating	EN 438-2
Resistance to immersion in boiling water (edge)				min. 3				rating	EN 438-2
Resistance to immersion in boiling water				max. 2 ^{3) 4)}				%	EN 438-2
Resistance to surface wear				min. 150				cycles	EN 438-2
Resistance to scratching (textured finishes)				min. 3				rating	EN 438-2
Resistance to impact by large diameter ball – impression diameter				max. 10				mm	EN 438-2
Resistance to impact by large diameter ball – Fall height				min. 1,800				mm	EN 438-2
Chemical resistance (SEFA 3 – Method A & B)				passed					SEFA 3:2020
Stain resistance (groups 1 & 2)				5				rating	EN 438-2
Stain resistance (group 3)				5				rating	EN 438-2
Resistance to colour change (xenon arc light)				4 to 5 Grey Scale Grade					EN 438-2
Reaction to fire				normally flammable					
Reaction to fire (Euroclass)				D-s2,d0					EN 13501-1, CWFT conforming to 2003/593/EG
Formaldehyde emission class				E1 E05					EN 717-1

¹⁾ Dirt, spots and similar surface defects

²⁾ Fibres, hairs and scratches

³⁾ Mass increase

⁴⁾ Thickness increase

Additional information

Product standard	<ul style="list-style-type: none"> EN 438-4
Areas of application	<ul style="list-style-type: none"> For demanding laboratory and work environments such as chemical research facilities, biological and analytical laboratories, pharmaceutical clean rooms, and quality control areas where exceptional robustness, high chemical resistance, and maximum hygiene standards are required. The material is also suitable for use in healthcare, the food industry, large-scale kitchens, and workshops where solvents, acids, alkalis, oils, or disinfectants are regularly used and therefore the highest durability and long-lasting resilience are essential. In addition, the material meets aesthetic and functional requirements in modern interior design concepts.
Core material	<ul style="list-style-type: none"> Compact laminate black Uniform black through-pigmented solid compact laminate core, impact resistant and moisture resistant for applications with high specification demands.

Technical data

Duropal HPL Compact LabSpec, black core

Product safety	<ul style="list-style-type: none"> This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. We manufacture the panels without the use of organohalogens, heavy metals, preservatives, wood protectors or organic solvents.
Special	<ul style="list-style-type: none"> The coarser the structure and the lighter the decor, the greater the scratch resistance. Depending on the decor and surface texture, slightly different surface visual impressions can result between cut panels viewed from different angles. This is a result of the production methods and does not constitute a quality defect. Especially for large applications, we recommend paying attention to the colour and texture uniformity of the boards and cut products used when further processing and installing and that the production direction is taken into account. Due to the black core of the material, minor decorative deviations to other products cannot be avoided. Due to the lacquered surface, minor decorative deviations to other products cannot be avoided. For production-related reasons, there may be minor colour variations in the black material core. Decor-structure-combination front side = Decor-structure-combination reverse side Subsequent oiling (with suitable cooking oil) of the machined edge can reduce machining and wear marks. Please note that in everyday use, polishing, scratches and shiny spots may occur due to mechanical stress, which are particularly visible on darker decors. This does not represent a quality defect or a restriction of usability. Rather, it reflects the natural ageing of the surface. The product complies with all requirements of EN 438.
Note	<ul style="list-style-type: none"> FSC certification or PEFC certification available on request. FSC license code: FSC® C011773 PEFC license code: PEFC/04-32-0828
Colour and surface match	<ul style="list-style-type: none"> Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2026 Pfleiderer Deutschland GmbH

This information is issued with great care. We do not however accept any responsibility for the accuracy, completeness and timeliness. There may be slight colour differences between the printed brochure image and the actual design.

Due to the continuous development and modification of our products, possible changes to the relevant standards, laws and regulations, our technical data sheets and product documents expressly do not represent a legally binding guarantee of the properties specified therein. In particular, no suitability for a specific purpose can be derived from this information. It is therefore the personal responsibility of the individual user to check the processing and suitability of the products described in this document for the intended use and to take into account the legal framework and the current state of the art. Furthermore, we expressly refer to the validity of our general terms and conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com

Pfleiderer Deutschland GmbH

Ingolstädter Str. 51
92318 Neumarkt
Germany

phone +49 (0) 91 81 28 48 0

Fax +49 (0) 91 81 28 48 2

info@pfleiderer.com

www.pfleiderer.com