

September 2023

Technical data Duropal HPL Compact, white core

Compact high-pressure laminate in standard quality according to EN 438-9:BCS. With uniform white-coloured core and decorative melamine resin surface on both sides.

N

Antimicrobial

High impact resistance

Applications






Certificates



Specification									Unit	Test standard
Nominal thickness	4	5	6	8	10	12	13	15	mm	
Tolerance on thickness	± 0.4	± 0.5	± 0.5	± 0.7	± 0.7	± 0.8	± 0.8	± 0.8	mm	EN 438-2
Tolerance on length				+	10			•	mm	EN 438-2
Tolerance on width	+ 10						mm	EN 438-2		
Surface defects	max. 1 ¹⁾ max. 10 ²⁾							mm²/m² mm/m²	EN 438-9	
Edge defects		max. 3						mm	EN 438-9	
Straightness of edges		max. 1.5					mm/m	EN 438-2		
Squareness	max. 1.5						mm/m	EN 438-2		
Flatness	max. 12	max. 12	max. 8	max. 8	max. 5	max. 5	max. 5	max. 5	mm/m	EN 438-2
Density	min. 1,400							kg/m³	EN ISO 1183-1	
Bending strength	min. 80					MPa	EN ISO 178			
lexural modulus	min. 9,000						MPa	EN ISO 178		
Resistance to crazing	min. 3 ³⁾ min. 4 ⁴⁾							rating	EN 438-2	
Dimensional stability at elevated temperature (length)	max. 0.6	max. 0.5	%	EN 438-2						
Dimensional stability at elevated emperature (width)	max. 1	max. 0.8	%	EN 438-2						
Resistance to dry heat, 160 °C other finishes)	min. 4						rating	EN 438-2		
Resistance to water vapour (oth- er finishes)	min. 4						rating	EN 438-2		
Resistance to immersion in boil- ng water (other finishes)	min. 4						rating	EN 438-2		

+49 (0) 91 81 28 48 0 +49 (0) 91 81 28 48 2 info@pfleiderer.com www.pfleiderer.com

phone Fax



Melamine impregnated decorative paper

Melamine impregnated decorative paper

Impregnated



September 2023

Technical data Duropal HPL Compact, white core

Specification									Unit	Test standard
Nominal thickness	4	5	6	8	10	12	13	15	mm	
Resistance to immersion in boil- ing water (edge)		1	1	mi	n. 3	<u>.</u>	1		rating	EN 438-2
Resistance to immersion in boil- ing water	max. 5 ⁵⁾ max. 6 ⁶⁾	max. 3 ⁵⁾ max. 4 ⁶⁾	max. 3 ⁵⁾ max. 4 ⁶⁾	max. 3 ⁵⁾ max. 4 ⁶⁾	max. 3 ⁵⁾ max. 4 ⁶⁾	max. 3 ⁵⁾ max. 4 ⁶⁾	max. 3 ⁵⁾ max. 4 ⁶⁾	max. 3 ⁵⁾ max. 4 ⁶⁾	%	EN 438-2
Resistance to surface wear				min	. 150				cycles	EN 438-2
Resistance to scratching (other finishes)	min. 3						rating	EN 438-2		
Stain resistance (groups 1 & 2)		min. 5						rating	EN 438-2	
Stain resistance (group 3)	min. 4						rating	EN 438-2		
Resistance to colour change (xenon arc light)	min. 3 Grey Scale Grade ³⁾ min. 4 Grey Scale Grade ⁴⁾								EN 438-2	
Reaction to fire	normally flammable									
Reaction to fire (Euroclass)	not classi- fied	not classi- fied	D- s2,d0	D- s2,d0	D- s2,d0	D- s2,d0	D- s2,d0	D- s2,d0		EN 13501-1, CWFT acc. to 2003/593/ EG
Formaldehyde emission class	E1 E05									

¹⁾ Dirt, spots and similar surface defects
²⁾ Fibres, hairs and scratches
³⁾ Edge/Core
⁴⁾ Texture
⁵⁾ For the second second

⁵⁾ Mass increase

⁶⁾ Thickness increase

Additional information

Product standard	• EN 438-9
Areas of application	 For unusual furniture and interior concepts in the home and contract sectors, in leisure and spa facilities, in shop design, in catering, as well as in humid and wet conditions in which particular robustness, durability and high hygienic standards including aesthetics are required of the material. The material is suitable for open edge solutions as well as for engraving for individual 3D effects.
Core material	 Compact laminate white core Uniform white through-pigmented solid compact laminate core, impact resistant and moisture resistant for applications with high specification demands.
Product safety	 The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011. The decorative surface and the core consists of paper layers, which are impregnated with thermosetting resins. The resins harden completely during the manufacturing process by heat and high pressure. They form a stable, resistant and non-reactive material. This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. We manufacture the panels without the use of halogens, heavy metals, preservatives, wood protectors or organic solvents.



September 2023

Technical data Duropal HPL Compact, white core

Antimicrobial effect	 Surface with antimicrobial effect in 24 h for interior fit-out and finishes – Test Methodology JIS Z 2801 / ISO 22196
Special	 NOV 22 150 Depending on the decor and surface texture, slightly different surface visual impressions can result between cut panels viewed from different angles. This is a result of the production methods and does not constitute a quality defect. Especially for large applications, we recommend paying attention to the colour and texture uniformity of the boards and cut products used when further processing and installing and that the production direction is taken into account. The smoother the structure and the the darker the decor, the more sensitive it is to stains. With intensive plain decors, especially in the red range, colour pigment wash-out may occur under certain circumstances. It is possible that colour pigments are not bound by the resin during the impregnation of the decor paper and are only deposited on the surface of the impregnate and are thus directly on the surface. If cleaning is then carried out, slight discolouration of the cleaning cloths can be observed. This is particularly the case when solvent-based cleaners are used. This is not a product defect. Due to the white core of the material, minor decorative deviations to other products cannot be avoided. For production-related reasons, there may be minor colour variations in the white material core. Due to the material core, Duropal HPL Compact with a white core are slightly harder and more brittle than Compact Worktops with a black material core. These will tend to warp more severely in case of climatic fluctuations. The uneven edge appearance is due to the structure depth of the texture Solid Granite caused by the product and does not represent a quality defect. Decor-structure-combination front side = Decor-structure-combination reverse side Subsequent oiling (with suitable cooking oil) of the machined edge can reduce machining and wear marks. Please note that in everyday use, polishing, scratches and shiny spots may occur due to mech
Note	 2,800 x 2,070 – FSC certification or PEFC certification available on request. 4,100 x 1,300 – With PEFC-certification. FSC license code: FSC[®] C011773 PEFC license code: PEFC/04-32-0828
Colour and surface match	 Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

Fax

© Copyright 2023 Pfleiderer Deutschland GmbH

This information has been compiled with the greatest care. Nevertheless we can assume no liability for the correctness, completeness and up-todateness of this information. Colour deviations caused by the printing technology are possible. In view of the ongoing further development and adaptation of our products, possible amendments to the relevant standards, laws and regulations, our technical data sheets and product documentation expressly do not constitute a legally binding assurance of the properties described there. In particular no guarantee of suitability for a concrete application can be derived. It is therefore the personal responsibility of the individual user in all cases to check the processing and suitability of the products described in this document for the intended application in advance, and to take into consideration the legal framework and the respective state-of-the-art. We furthermore expressly draw attention to the applicability of our General Terms and Conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com

Pfleiderer Deutschland GmbH
Ingolstädter Str. 51
92318 Neumarkt
Germany

+49 (0) 91 81 28 48 0 phone +49 (0) 91 81 28 48 2 info@pfleiderer.com www.pfleiderer.com