


Technical data

Duropal HPL ESA

Electrostatically dissipative high-pressure laminate in postforming quality in accordance with EN 438-3:HGP/VGP, with robust melamine resin surface and sanded reverse.

Applications



Properties



Certificates



Specification			Unit	Test standard
Nominal thickness	0.6	0.8	mm	
Tolerance on thickness	± 0.1		mm	EN 438-2
Tolerance on length	+ 10		mm	EN 438-2
Tolerance on width	+ 10		mm	EN 438-2
Surface defects	max. 1 ¹⁾ max. 10 ²⁾		mm ² /m ² mm/m ²	EN 438-2
Edge defects	max. 20		mm	EN 438-2
Straightness of edges	max. 1.5		mm/m	EN 438-2
Squareness	max. 1.5		mm/m	EN 438-2
Flatness (length)	max. 60		mm/m	EN 438-2
Density	min. 1,350		kg/m ³	EN ISO 1183-1
Dimensional stability at elevated temperature (length)	max. 0.55		%	EN 438-2
Dimensional stability at elevated temperature (width)	max. 1.05		%	EN 438-2
Resistance to dry heat, 160 °C (other finishes)	min. 4		rating	EN 438-2
Resistance to surface wear	min. 150		cycles	EN 438-2
Resistance to scratching (textured finishes)	min. 3		rating	EN 438-2
Resistance to impact (small diameter ball)	min. 20		N	EN 438-2
Stain resistance (groups 1 & 2)	min. 5		rating	EN 438-2
Stain resistance (group 3)	min. 4		rating	EN 438-2
Resistance to colour change (xenon arc light)	4 to 5 Grey Scale Grade			EN 438-2
Reaction to fire	normally flammable			
Reaction to fire (Euroclass)	Euroclass D-s2,d0 or worse in connection with normally and easily inflammable core boards.			EN 13501-1, CWFT conforming to 2003/593/EG

Technical data

Duropal HPL ESA

Specification		Unit	Test standard
Nominal thickness	0.6	0.8	mm
Volume resistance R_D	$1 \times 10^4 - 1 \times 10^9 \text{ Ohm}^{3)}$		EN 61340-5-1
Formaldehyde emission class	E1 E05		EN 717-1
Formability (length)	min. $10 \times t^{4)}$		EN 438-2
Formability (width)	Not determined, processing tests are to be carried out.		

¹⁾ Dirt, spots and similar surface defects

²⁾ Fibres, hairs and scratches

³⁾ measured dry, measurement voltage 100 V DC, cylindrical electrode, 20–30 °C and 20–50 % rel. humidity (96 h conditioning)

⁴⁾ t = nominal thickness

Additional information

Product standard	<ul style="list-style-type: none"> in accordance with EN 438-3
Areas of application	<ul style="list-style-type: none"> The products from our ESA system are indispensable wherever electrostatic charges are to be prevented. The conductive constituents in the core plate and facing ensure a reliable and simple earthing possibility for furniture components and worktops in ESD areas, on production and assembly lines, in laboratories or central control rooms.
Product safety	<ul style="list-style-type: none"> This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011. The decorative surface and the core consists of paper layers, which are impregnated with thermosetting resins. The resins harden completely during the manufacturing process by heat and high-pressure. They form a stable, resistant and non-reactive material.
Antimicrobial effect	<ul style="list-style-type: none"> Surface with antimicrobial effect in 24 h for interior fit-out and finishes – Test Methodology JIS Z 2801 / ISO 22196
Special	<ul style="list-style-type: none"> The coarser the structure and the lighter the decor, the greater the scratch resistance. Depending on the decor and surface texture, slightly different surface visual impressions can result between cut panels viewed from different angles. This is a result of the production methods and does not constitute a quality defect. Especially for large applications, we recommend paying attention to the colour and texture uniformity of the boards and cut products used when further processing and installing and that the production direction is taken into account. Classification HGP / HGS / HGF is achieved with the surface textures recommended for horizontal applications. Requirements of classification VGP / VGS / VGF are met by all surface textures. Please refer to our sales documentation, to check which textures are available for this product. Decors: W10140 Frontal White / U12188 Light Grey
Note	<ul style="list-style-type: none"> FSC certification or PEFC certification available on request. FSC license code: FSC® C011773 PEFC license code: PEFC/04-32-0828
Colour and surface match	<ul style="list-style-type: none"> Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Technical data

Duropal HPL ESA

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2025 Pfleiderer Deutschland GmbH

This information is issued with great care. We do not however accept any responsibility for the accuracy, completeness and timeliness. There may be slight colour differences between the printed brochure image and the actual design.

Due to the continuous development and modification of our products, possible changes to the relevant standards, laws and regulations, our technical data sheets and product documents expressly do not represent a legally binding guarantee of the properties specified therein. In particular, no suitability for a specific purpose can be derived from this information. It is therefore the personal responsibility of the individual user to check the processing and suitability of the products described in this document for the intended use and to take into account the legal framework and the current state of the art. Furthermore, we expressly refer to the validity of our general terms and conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com

Pfleiderer Deutschland GmbH

Ingolstädter Str. 51
92318 Neumarkt
Germany

phone	+49 (0) 91 81 28 48 0
Fax	+49 (0) 91 81 28 48 2
	info@pfleiderer.com
	www.pfleiderer.com