

Technical data

Duropal HPL microPLUS®

Decorative high pressure laminate in postforming quality according to EN 438-3:HGP/VGP, with robust melamine resin surface and an antimicrobial and antiviral surface finish (Sanitized® Silver) and sanded reverse.

Melamine impregnated decorative paper with antimicrobial and antiviral surface microPLUS®

Impregnated craft paper, reverse side sanded

Applications



Furniture and interior fitting



Doors

Properties



Variety of decors and / or textures



Easy care



Antimicrobial



Food harmless

Certificates



Specification				Unit	Test standard
Nominal thickness	0.6	0.8	1.2	mm	
Tolerance on thickness	± 0.1	± 0.1	± 0.15	mm	EN 438-2
Tolerance on length		+ 10		mm	EN 438-2
Tolerance on width		+ 10		mm	EN 438-2
Surface defects		max. 1 ¹⁾ max. 10 ²⁾		mm ² /m ² mm/m ²	EN 438-2
Edge defects		max. 20		mm	EN 438-2
Straightness of edges		max. 1.5		mm/m	EN 438-2
Squareness		max. 1.5		mm/m	EN 438-2
Flatness (length)		max. 60		mm/m	EN 438-2
Density		min. 1,350		kg/m ³	EN ISO 1183-1
Dimensional stability at elevated temperature (length)		max. 0.55 ³⁾ max. 0.75 ⁴⁾		%	EN 438-2
Dimensional stability at elevated temperature (width)		max. 1.05 ³⁾ max. 1.25 ⁴⁾		%	EN 438-2
Resistance to wet heat, 100 °C (gloss finishes)		min. 3		rating	EN 438-2
Resistance to wet heat, 100 °C (other finishes)		min. 4		rating	EN 438-2
Resistance to dry heat, 160 °C (gloss finishes)		min. 3		rating	EN 438-2
Resistance to dry heat, 160 °C (other finishes)		min. 4		rating	EN 438-2
Resistance to water vapour (gloss finishes)		min. 3		rating	EN 438-2
Resistance to water vapour (other finishes)		min. 4		rating	EN 438-2
Resistance to immersion in boiling water (gloss finishes)		min. 3		rating	EN 438-2

Technical data

Duropal HPL microPLUS®

Specification				Unit	Test standard
Nominal thickness	0.6	0.8	1.2	mm	
Resistance to immersion in boiling water (other finishes)	min. 4			rating	EN 438-2
Resistance to surface wear	min. 50 ⁴⁾ min. 150 ³⁾			cycles	EN 438-2
Resistance to scratching (smooth finishes)	min. 1 ⁴⁾ min. 2 ³⁾			rating	EN 438-2
Resistance to scratching (textured finishes)	min. 2 ⁴⁾ min. 3 ³⁾			rating	EN 438-2
Resistance to impact (small diameter ball)	min. 15 ⁴⁾ min. 20 ³⁾			N	EN 438-2
Stain resistance (groups 1 & 2)	min. 5			rating	EN 438-2
Stain resistance (group 3)	min. 4			rating	EN 438-2
Resistance to colour change (xenon arc light)	4 to 5 Grey Scale Grade				EN 438-2
Reaction to fire	normally flammable				
Reaction to fire (Euroclass)	Euroclass D-s2,d0 or worse in connection with normally and easily inflammable core boards.				EN 13501-1, CWFT acc. to 2003/593/EG
Formaldehyde emission class	E1 E05				EN 717-1
Formability (length)	min. 10 x t ⁵⁾	min. 10 x t ⁵⁾	min. 10 x t ⁵⁾ Depending on decor and structure – processing tests are to be carried out		EN 438-2
Formability (width)	Not determined, processing tests are to be carried out.				

¹⁾ Dirt, spots and similar surface defects

²⁾ Fibres, hairs and scratches

³⁾ Classification HGP

⁴⁾ Classification VGP

⁵⁾ t = nominal thickness

Additional information

Product standard	<ul style="list-style-type: none"> EN 438-3
Areas of application	<ul style="list-style-type: none"> Surface material for high quality kitchen and office furniture, for walls and doors, furniture and installations in retail and recreational facilities, in the restaurant sector, in administration buildings, day nurseries, schools, sanitary, clinical or laboratory sectors. Particularly where high demands are made on sturdiness, ease of care and hygiene.
Product safety	<ul style="list-style-type: none"> This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011. The decorative surface and the core consists of paper layers, which are impregnated with thermosetting resins. The resins harden completely during the manufacturing process by heat and high pressure. They form a stable, resistant and non-reactive material.
Antimicrobial effect	<ul style="list-style-type: none"> Surface with antimicrobial effect in 7 h for interior fit-out and finishes – Test Methodology JIS Z 2801 / ISO 22196

Technical data

Duropal HPL microPLUS®

Antiviral effect	<ul style="list-style-type: none"> Surface with antiviral effect against enveloped viruses in 24 h for interior fit-out and finishes - Test Methodology ISO 21702:2019
Special	<ul style="list-style-type: none"> The coarser the structure and the lighter the decor, the greater the scratch resistance. The smoother the structure and the the darker the decor, the more sensitive it is to stains. Depending on the decor and surface texture, slightly different surface visual impressions can result between cut panels viewed from different angles. This is a result of the production methods and does not constitute a quality defect. Especially for large applications, we recommend paying attention to the colour and texture uniformity of the boards and cut products used when further processing and installing and that the production direction is taken into account. With intensive plain decors, especially in the red range, colour pigment wash-out may occur under certain circumstances. It is possible that colour pigments are not bound by the resin during the impregnation of the decor paper and are only deposited on the surface of the impregnate and are thus directly on the surface. If cleaning is then carried out, slight discolouration of the cleaning cloths can be observed. This is particularly the case when solvent-based cleaners are used. This is not a product defect. Sanitized® Silver is based on the natural effect of silver, embedded in a patented glass-ceramic. This additive is free of nanoparticles and is incorporated as a dispersion into the resin of our decor / overlay papers. Sanitized® Silver remains in the product and does not wash out. The effect is ensured over the whole life cycle of the product. Classification HGP / HGS / HGF is achieved with the surface textures recommended for horizontal applications. Requirements of classification VGP / VGS / VGF are met by all surface textures. Please refer to our sales documentation, to check which textures are available for this product.
Note	<ul style="list-style-type: none"> FSC certification or PEFC certification available on request. FSC license code: FSC® C011773 PEFC license code: PEFC/04-32-0828
Colour and surface match	<ul style="list-style-type: none"> Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2023 Pfleiderer Deutschland GmbH

This information has been compiled with the greatest care. Nevertheless we can assume no liability for the correctness, completeness and up-to-dateness of this information. Colour deviations caused by the printing technology are possible. In view of the ongoing further development and adaptation of our products, possible amendments to the relevant standards, laws and regulations, our technical data sheets and product documentation expressly do not constitute a legally binding assurance of the properties described there. In particular no guarantee of suitability for a concrete application can be derived. It is therefore the personal responsibility of the individual user in all cases to check the processing and suitability of the products described in this document for the intended application in advance, and to take into consideration the legal framework and the respective state-of-the-art. We furthermore expressly draw attention to the applicability of our General Terms and Conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com

Pfleiderer Deutschland GmbH

Ingolstädter Str. 51
92318 Neumarkt
Germany

phone +49 (0) 91 81 28 48 0
Fax +49 (0) 91 81 28 48 2
info@pfleiderer.com
www.pfleiderer.com