





May 2023

Technical data Duropal Worktop Quadra microPLUS® Hydrofuge MR

Worktop consisting of a moisture-resistant particleboard type P2 to EN 312, decor side bonded with robust Duropal HPL microPLUS® with an antimicrobial and antiviral surface finish (Sanitized® Silver) according to EN 438, underside with waterrepellent backing. The postforming front edge of the Quadra worktop has a radius of 3 mm, the rear edge is sealed with a protective edge. It is also available as a variant with both sides profiled.



Applications



Certificates



Specification					Unit	Test standard
Nominal thickness	38	38	38	38	mm	
Width	600	650	900	1,200	mm	
Tolerance on thickness	± 0.4				mm	ISO 13894-1
Tolerance on length	± 5			mm	ISO 13894-1	
Surface defects – HPL	max. 1 ¹⁾ max. 10 ²⁾				mm²/m² mm/m²	EN 438-2
Straightness of edges	± 0.5				mm/m	ISO 13894-1
Squareness	≤ 2			mm/m	ISO 13894-1	
Flatness (length)	≤ 2				mm/m	ISO 13894-1
Flatness (width)	≤ 0.9	≤ 1.1	≤ 1.6	≤ 2	mm mm/m	ISO 13894-1
Resistance to wet heat, 100 °C (other finishes) – HPL	min. 4				rating	EN 438-2
Resistance to dry heat, 160 °C (other finishes) – HPL	min. 4			rating	EN 438-2	
Resistance to water vapour (oth- er finishes) – HPL	min. 4			rating	EN 438-2	
Resistance to surface wear – HPL	min. 150			cycles	EN 438-2	
Resistance to scratching (smooth finishes) – HPL	min. 2			rating	EN 438-2	
Resistance to scratching (tex- tured finishes) – HPL	min. 3			rating	EN 438-2	
Resistance to impact (small di- ameter ball)	≥ 15			Ν	ISO 13894-1	

+49 (0) 91 81 28 48 0 +49 (0) 91 81 28 48 2 info@pfleiderer.com www.pfleiderer.com

phone

Fax



May 2023

Technical data Duropal Worktop Quadra microPLUS® Hydrofuge MR

Specification					Unit	Test standard
Nominal thickness	38	38	38	38	mm	
Width	600	650	900	1,200	mm	
Stain resistance (groups 1 & 2) – HPL	min. 5				rating	EN 438-2
Stain resistance (group 3) – HPL	min. 4				rating	EN 438-2
Resistance to colour change (xenon arc light) – HPL	4 to 5 Grey Scale Grade					EN 438-2
Reaction to fire (Euroclass)	not classified					
Formaldehyde emission class	E1 E05 CARB Phase 2 / TSCA Title VI					EN 717-1
Mean density	580 - 540 ³⁾				kg/m³	EN 323
Raw core materials	8.5 ³⁾				N/mm ²	EN 310
Modulus of elasticity (bending stiffness)	1,200 ³⁾				N/mm²	EN 310
Internal bond	0.2 3)				N/mm²	EN 319
Surface soundness	0.8 3)				N/mm ²	EN 311
Durability – Water resistance	≤ 15				%	ISO 13894-1
Resistance to fixings (face)	≥ 1,500			N	ISO 13894-1	
Resistance to fixings (edge)	≥ 500				N	ISO 13894-1
Bonding strength	≥ 0.6				N/mm ²	ISO 13894-1
Flexural tensile strength	≥ 0.6				N/mm²	ISO 13894-1
Durability – Glue-line quality	≥ 3				rating	ISO 13894-1
Durability – Resistance to elevat- ed temperature	no effect					ISO 13894-1

¹⁾ Dirt, spots and similar surface defects ²⁾ Fibres, hairs and scratches

³⁾ Core material

Additional information

Product standard	• EN 13894-1				
Areas of application	 Duropal worktops can be used wherever very high demands are made on surface resistance and durability. Thanks to their hygienic advantages, the classic areas of application are in modern kitchens and bathrooms, canteens and restaurants, as well as doctors' surgeries, in laboratories and shop fitting, but also for industrial and commercial workplaces. 				
Core material	 ClassicBoard Hydrofuge MR CARB2 Low Emission urea resin-bonded furniture board with reduced thickness swelling according to DIN EN 312, suitable for non-load-bearing use in humid conditions. 				
Product safety	 This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011. 				
Antimicrobial effect	Surface with antimicrobial effect in 7 h for interior fit-out and finishes – Test Methodology JIS Z 2801 / ISO 22196				





May 2023

Technical data Duropal Worktop Quadra microPLUS® Hydrofuge MR

Antiviral effect	 Surface with antiviral effect against enveloped viruses in 24 h for interior fit-out and finishes - Test Methodology ISO 21702:2019 			
Special	 Sanitized[®] Silver is based on the natural effect of silver, embedded in a patented glass-ceramic. This additive is free of nanoparticles and is incorporated as a dispersion into the resin of our decor / overlay papers. 			
	 Sanitized[®] Silver remains in the product and does not wash out. The effect is ensured over the whole life cycle of the product. 			
Note	FSC certification or PEFC certification available on request.			
	 FSC license code: FSC[®] C011773 PEFC license code: PEFC/04-32-0828 			
Colour and surface match	 Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. 			
	 The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually. 			

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

Fax

© Copyright 2023 Pfleiderer Deutschland GmbH

This information has been compiled with the greatest care. Nevertheless we can assume no liability for the correctness, completeness and up-todateness of this information. Colour deviations caused by the printing technology are possible. In view of the ongoing further development and adaptation of our products, possible amendments to the relevant standards, laws and regulations, our technical data sheets and product documentation expressly do not constitute a legally binding assurance of the properties described there. In particular no guarantee of suitability for a concrete application can be derived. It is therefore the personal responsibility of the individual user in all cases to check the processing and suitability of the products described in this document for the intended application in advance, and to take into consideration the legal framework and the respective state-of-the-art. We furthermore expressly draw attention to the applicability of our General Terms and Conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com