


November 2025

Technical data

Duropal Worktop Quadra microPLUS® P2

Worktop consisting of a particleboard type P2 conforming to EN 312, decor side surfaced with Duropal HPL microPLUS® – an antimicrobial and antiviral surface finish (Sanitized® Silver), underside with moisture-resistant backing. The postforming front edge of the Quadra worktop has a radius of 3 mm, the rear edge is sealed with a protective edge. It is also available as a variant with both sides profiled.



Applications



Properties



Variety of decors and / or textures



Easy care





Food harmless

Certificates





Specification							Unit	Test standard
Nominal thickness	28	28	28	38	38	38	mm	
Width	600	900	1,200	600	900	1,200	mm	
Tolerance on thickness	± 0.4					mm		
Tolerance on length	± 5					mm	ISO 13894-1	
Tolerance on width	±0.5 mm at 500 mm, with an additional 0.05 mm for every extra 100 mm						ISO 13894-1	
Surface defects – HPL	max. 1 ¹⁾ max. 10 ²⁾					mm²/m² mm/m²	EN 438-2	
Straightness of edges	± 0.5					mm/m	ISO 13894-1	
Squareness	≤2					mm/m	ISO 13894-1	
Flatness (length)	max. 2					mm/m	ISO 13894-1	
Flatness (width)	max. 2					mm/m	ISO 13894-1	
Resistance to wet heat, 100 °C (other finishes) – HPL	min. 4					rating	EN 438-2	
Resistance to dry heat, 160 °C (other finishes) – HPL	min. 4					rating	EN 438-2	
Resistance to water vapour (other finishes) – HPL	min. 4					rating	EN 438-2	
Resistance to surface wear – HPL	min. 150					cycles	EN 438-2	
Resistance to scratching (smooth finishes) – HPL	min. 2					rating	EN 438-2	
Resistance to scratching (tex- tured finishes) – HPL	min. 3					rating	EN 438-2	
Resistance to impact (small di- ameter ball)	min. 15					N	ISO 13894-1	
Stain resistance (groups 1 & 2) – HPL	min. 5					rating	EN 438-2	



November 2025

Technical data

Duropal Worktop Quadra microPLUS® P2

Specification							Unit	Test standard
Nominal thickness	28	28	28	38	38	38	mm	
Width	600	900	1,200	600	900	1,200	mm	
Stain resistance (group 3) – HPL	min. 4						rating	EN 438-2
Resistance to colour change (xenon arc light) – HPL	4 to 5 Grey Scale Grade						EN 438-2	
Reaction to fire (Euroclass)	not classified							
Formaldehyde emission class	E1 E05 TSCA Title VI							EN 717-1
Mean density	600 - 580 ³⁾	600 - 580 ³⁾	600 - 580 ³⁾	580 - 540 ³⁾	580 - 540 ³⁾	580 - 540 ³⁾	kg/m³	EN 323
Bending strength	9.5 ³⁾	9.5 ³⁾	9.5 ³⁾	8.5 ³⁾	8.5 ³⁾	8.5 ³⁾	N/mm²	EN 310
Modulus of elasticity (bending stiffness)	1,350 ³⁾	1,350 ³⁾	1,350 ³⁾	1,200 ³⁾	1,200 ³⁾	1,200 ³⁾	N/mm²	EN 310
Internal bond	0.25 ³⁾	0.25 ³⁾	0.25 ³⁾	0.2 ³⁾	0.2 ³⁾	0.2 ³⁾	N/mm²	EN 319
Bonding strength	≥ 0.8						N/mm²	ISO 13894-1
Durability – Glue-line quality	≥3					rating	ISO 13894-1	
Durability – Resistance to elevated temperature	no effect						ISO 13894-1	

¹⁾ Dirt, spots and similar surface defects

Additional information

Product standard	in accordance with EN 13894-2
Areas of application	 Duropal Worktops can be used wherever very high demands are made on surface resistance and durability. Thanks to their hygienic advantages, the classic areas of application are in modern kitchens and bathrooms, canteens and restaurants as well as doctors' surgeries, in laboratories and shop fitting, but also for industrial and commercial workplaces.
Core material	 ClassicBoard P2 Urea resin-bonded particleboard, type P2 conforming to EN 312, suitable for non load-bearing purposes in dry areas.
Product safety	 This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011. The decorative surface and the core consists of paper layers, which are impregnated with thermosetting resins. The resins harden completely during the manufacturing process by heat and high-pressure. They form a stable, resistant and non-reactive material.
Antimicrobial effect	Surface with antimicrobial effect in 7 h for interior fit-out and finishes – Test Methodology JIS Z 2801 / ISO 22196

²⁾ Fibres, hairs and scratches

³⁾ Core material



November 2025

Technical data

Duropal Worktop Quadra microPLUS® P2

Antiviral effect	 Surface with antiviral effect against enveloped viruses in 24 h for interior fit-out and finishes - Test Methodology ISO 21702:2019
Special	 The coarser the structure and the lighter the decor, the greater the scratch resistance. The smoother the structure and the the darker the decor, the more sensitive it is to stains. Depending on the decor and surface texture, slightly different surface visual impressions can result between cut panels viewed from different angles. This is a result of the production methods and does not constitute a quality defect. Especially for large applications, we recommend paying attention to the colour and texture uniformity of the boards and cut products used when further processing and installing and that the production direction is taken into account. With intensive plain decors, especially in the red range, colour pigment wash-out may occur under certain circumstances. It is possible that colour pigments are not bound by the resin during the impregnation of the decor paper and are only deposited on the surface of the impregnate and are thus directly on the surface. If cleaning is then carried out, slight discolouration of the cleaning cloths can be observed. This is particularly the case when solvent-based cleaners are used. This is not a product defect. Sanitized[®] Silver is based on the natural effect of silver, embedded in a patented glass-ceramic. This additive is free of nanoparticles and is incorporated as a dispersion into the resin of our decor / overlay papers. Sanitized[®] Silver remains in the product and does not wash out. The effect is ensured over the whole life cycle of the product.
Note	FSC certification or PEFC certification available on request. FSC license code: FSC® C011773 PEFC license code: PEFC/04-32-0828
Colour and surface match	 Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2025 Pfleiderer Deutschland GmbH

This information is issued with great care. We do not however accept any responsibility for the accuracy, completeness and timeliness. There may be slight colour differences between the printed brochure image and the actual design.

Due to the continuous development and modification of our products, possible changes to the relevant standards, laws and regulations, our technical data sheets and product documents expressly do not represent a legally binding guarantee of the properties specified therein. In particular, no suitability for a specific purpose can be derived from this information. It is therefore the personal responsibility of the individual user to check the processing and suitability of the products described in this document for the intended use and to take into account the legal framework and the current state of the art. Furthermore, we expressly refer to the validity of our general terms and conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com