

Technical data

FormBoard P7 S


Chipboard type P7 according to DIN EN 312, highly load-bearing, for structural use in humid environments, coated on both sides with melamine. Standard resin application per side approx. 320 g/m², or on request approx. 450 g/m².



Applications



Properties



Low swelling / moisture resistant



Load bearing – particularly high bending strength



Direction-free application

Certificates



Specification			Unit	Test standard
Nominal thickness	17.5	20.5	mm	
Tolerance on thickness	±0.3 for class 1, 2 +0.5/-0.3 for class 3A, 3B, 4 and gloss surfaces	±0,5	mm	EN 14323
Length- and width tolerance	± 5		mm	EN 14323
Length- and width tolerance (pre-cut panels)	± 2.5		mm	EN 14323
Flatness	≤ 2 ¹⁾		mm/m	EN 14323
Edge damage	≤ 10		mm	EN 14323
Edge damage (pre-cut panels)	≤ 3		mm	EN 14323
Surface defects (Points)	≤ 2		mm ² /m ²	EN 14323
Surface defects (Defect in the length)	≤ 20		mm/m	EN 14323
Resistance to scratching	≥ 1.5 ²⁾		N	EN 14323
Resistance to staining	min. 3		Rating	EN 14323
Resistance to cracking	min. 3		Rating	EN 14323
Resistance to abrasion (plain colours)	3A		Class	EN 14323
Resistance to abrasion (printed designs)	1		Class	EN 14323
Resistance to colour change in xenon arc light	min. 4 Grey Scale Grade ³⁾			EN 14323
Mean density	760 ⁴⁾		kg/m ³	EN 323
Density tolerance	± 10 ⁴⁾		%	EN 323
Bending strength	23 ⁴⁾		N/mm ²	EN 310
Bending modulus of elasticity	3,100 ⁴⁾	2,900 ⁴⁾	N/mm ²	EN 310
Internal bond	0.7 ⁴⁾	0.65 ⁴⁾	N/mm ²	EN 319

Technical data

FormBoard P7 S

Specification			Unit	Test standard
Nominal thickness	17.5	20.5	mm	
Internal bond after boil test	0.2 ⁴⁾		N/mm ²	EN 1087-1
Thickness swell (24 h)	5 ⁴⁾	4 ⁴⁾	%	EN 317
Formaldehyde release	E1 E05			
Reaction to fire (Euroclass)	D-s2,d0 conforming to EN 13986 dependent on end use (Thickness: ≥ 9 mm / Gross density: ≥ 600 kg/m ³)			

¹⁾ If symmetrical construction

²⁾ Except smooth and matt structures, as well as decors with mother-of-pearl effect

³⁾ Except for metallic decors

⁴⁾ Core material

Additional information

Product standard	<ul style="list-style-type: none"> EN 14322
Areas of application	<ul style="list-style-type: none"> FormBoard P7 S is ideally suited for repeated use in formwork construction thanks to its moisture-resistant bonding. An optimal result is supported by a special impregnation of the coating. The standard version features approx. 320 g/m² per side, while a variant with approx. 450 g/m² increases the number of possible usage cycles (up to 25 uses)! The setting behavior of the concrete is not negatively affected by the board.
Core material	<ul style="list-style-type: none"> PremiumBoard P7 S Wood particleboard type P7 in accordance with EN 312, heavy-duty for structural purposes for use in humid conditions.
Product safety	<ul style="list-style-type: none"> This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. The surface is physiologically safe, and approved for direct contact with food acc. to Regulation (EU) No. 10/2011. We manufacture the panels without the use of organohalogens, heavy metals, preservatives, wood protectors or organic solvents.
Resistance to heat	<ul style="list-style-type: none"> Heat sources (e.g. coffee machines, printers, fax machines, etc.) should not come into direct contact with the board, otherwise cracks may form due to drying out. For continuous exposure to heat, temperatures of up to 50°C are permissible. In the case of permanent exposure to heat, we expressly draw attention to the risk of cracking.
Special	<ul style="list-style-type: none"> A protective foil must be removed as soon as possible after processing – but at the latest within 6 months after delivery – to ensure residue-free removal of the foil. In addition, foiled boards must not be exposed to direct sunlight (UV radiation).
Note	<ul style="list-style-type: none"> FSC certification or PEFC certification available on request. FSC license code: FSC® C011773 PEFC license code: PEFC/04-32-0828
Processing instructions	<ul style="list-style-type: none"> Thick and thin edges are suitable.
Colour and surface match	<ul style="list-style-type: none"> Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually.

Technical data

FormBoard P7 S

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

© Copyright 2026 Pfleiderer Deutschland GmbH

This information is issued with great care. We do not however accept any responsibility for the accuracy, completeness and timeliness. There may be slight colour differences between the printed brochure image and the actual design.

Due to the continuous development and modification of our products, possible changes to the relevant standards, laws and regulations, our technical data sheets and product documents expressly do not represent a legally binding guarantee of the properties specified therein. In particular, no suitability for a specific purpose can be derived from this information. It is therefore the personal responsibility of the individual user to check the processing and suitability of the products described in this document for the intended use and to take into account the legal framework and the current state of the art. Furthermore, we expressly refer to the validity of our general terms and conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com

Pfleiderer Deutschland GmbH

Ingolstädter Str. 51
92318 Neumarkt
Germany

phone +49 (0) 91 81 28 48 0
Fax +49 (0) 91 81 28 48 2
info@pfleiderer.com
www.pfleiderer.com