

Technical data

PremiumBoard MFP P5

Tolerance on thickness	± 0.3 mm
Tolerance on length (EN 324-1)	± 5 mm
Tolerance on width (EN 324-1)	± 5 mm
Straightness of edges (EN 324-2)	1.5 mm/m
Squareness (EN 324-2)	2 mm/m
Moisture content (EN 322)	9 % ± 4 %
Formaldehyde emission class	E1 E05

Property	Test method	Unit	Requirement						
			Thickness / Range of thickness (mm, nominal dimension)						
			> 8.9 to ≤ 10	> 10 to ≤ 13	> 13 to ≤ 20	> 20 to ≤ 25	> 25 to ≤ 32	> 32 to ≤ 40	> 40
Mean density	EN 323	kg/m ³	790 – 690	770 – 680	700 – 660	670 – 650	660 – 640	640 – 620	≤ 620
Bending strength	EN 310	N/mm ²	18	18	16	14	12	10	9
Bending modulus of elasticity	EN 310	N/mm ²	2,550	2,550	2,400	2,150	1,900	1,700	1,550
Internal bond	EN 319	N/mm ²	0.45	0.45	0.45	0.4	0.35	0.3	0.25
Swelling in thickness, 24 h	EN 317	%	13	11	10	10	10	9	9
Internal bond after boil test	EN 1087-1	N/mm ²	0.15	0.15	0.14	0.12	0.11	0.1	0.09

© Copyright 2025 Pfleiderer Deutschland GmbH

This information is issued with great care. We do not however accept any responsibility for the accuracy, completeness and timeliness. There may be slight colour differences between the printed brochure image and the actual design.

Due to the continuous development and modification of our products, possible changes to the relevant standards, laws and regulations, our technical data sheets and product documents expressly do not represent a legally binding guarantee of the properties specified therein. In particular, no suitability for a specific purpose can be derived from this information. It is therefore the personal responsibility of the individual user to check the processing and suitability of the products described in this document for the intended use and to take into account the legal framework and the current state of the art. Furthermore, we expressly refer to the validity of our general terms and conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com